

A Review On- Economic Feasibility and Potential Environmental Benefits of Large-Scale Bamboo Leaves Ash Utilization Will Be Critical for Its Widespread Adoption

MANU S E¹, DASARATHY A K² AND DEVADATHAN N C³

¹Research Scholar, Department of Civil Engineering, FET, JAIN (Deemed-to-be University), Bengaluru-562112, Karnataka, India

²Professor & HOD, Department of Civil Engineering, FET, JAIN (Deemed-to-be University), Bengaluru-562112, Karnataka, India

³PG Scholar, Department of Civil Engineering, FET, JAIN (Deemed-to-be University), Bengaluru-562112, Karnataka, India

Abstract

The construction industry is one of the largest consumers of natural resources and a significant contributor to global carbon dioxide emissions, primarily due to cement production. Supplementary Cementitious Materials (SCMs) have emerged as sustainable alternatives to reduce cement consumption and mitigate environmental impacts. Bamboo Leaf Ash (BLA), produced through controlled combustion of bamboo leaves, has gained considerable attention owing to its high silica content and pozzolanic characteristics. Bamboo is widely available in tropical and subtropical regions, generating substantial biomass waste that is often disposed of through open burning or landfilling. Converting bamboo leaves into ash provides a sustainable waste management solution while creating value-added construction materials.

This review critically evaluates the economic feasibility and environmental benefits associated with large-scale utilization of Bamboo Leaf Ash as a partial replacement for cement in concrete. The study synthesizes findings from recent research on the physical, chemical, mechanical, environmental, and economic aspects of BLA incorporation in concrete. Particular emphasis is placed on production costs, transportation considerations, carbon footprint reduction, waste diversion, energy savings, and lifecycle environmental impacts.

The review reveals that replacement levels between 5–15% BLA can maintain or improve concrete performance while significantly reducing cement demand. Life Cycle Assessment (LCA) studies indicate considerable reductions in greenhouse gas emissions and embodied energy. Economic analyses demonstrate that the use of locally available bamboo waste can lower material costs and provide additional income opportunities in rural areas. However, challenges such as quality control, large-scale processing infrastructure, standardization, and supply chain management remain barriers to widespread implementation.

The findings suggest that Bamboo Leaf Ash possesses substantial potential to become an environmentally sustainable and economically viable supplementary cementitious material, contributing to circular economy principles and low-carbon construction practices.

Keywords: Bamboo Leaf Ash, Supplementary Cementitious Material, Sustainable Concrete, Economic Feasibility, Carbon Emissions, Circular Economy, Life Cycle Assessment.

Introduction

Global Cement Industry and Environmental Challenges

The construction sector accounts for nearly 40% of global resource consumption and approximately 8% of worldwide CO₂ emissions originate from cement manufacturing. Ordinary Portland Cement (OPC) production involves calcination of limestone and high-temperature clinker production, resulting in significant energy consumption and greenhouse gas emissions.

Growing urbanization and infrastructure development continue to increase cement demand globally. Consequently, researchers and policymakers are seeking alternative materials capable of reducing environmental impacts without compromising structural performance.

Role of Supplementary Cementitious Materials (SCMs)

SCMs are materials possessing pozzolanic or latent hydraulic properties that react with calcium hydroxide released during cement hydration.

Common SCMs include:

- i. Fly Ash (FA)
- ii. Ground Granulated Blast Furnace Slag (GGBS)
- iii. Silica Fume (SF)
- iv. Rice Husk Ash (RHA)
- v. Palm Oil Fuel Ash (POFA)
- vi. Bamboo Leaf Ash (BLA)

The utilization of SCMs contributes to:

- i. Reduction in cement consumption
- ii. Lower carbon emissions
- iii. Improved durability
- iv. Enhanced waste utilization
- v. Conservation of natural resources



Figure-1: Drying of Bamboo Leaves



Figure-2: Open Air Burning of Bamboo Leaves

Bamboo is among the fastest-growing plants globally, capable of growing up to 1 meter per day under favourable conditions. More than 1,600 bamboo species exist worldwide, with significant cultivation in:

- i.India
- ii.China
- iii.Indonesia
- iv.Vietnam
- v.Thailand
- vi.Brazil

India possesses approximately 15 million hectares of bamboo resources, generating substantial quantities of leaf litter annually.

Bamboo Leaf Ash as a Sustainable SCM

Bamboo leaves contain high concentrations of amorphous silica. Controlled combustion at temperatures between 500–700°C produces ash rich in reactive silica, making it suitable as a pozzolanic material.

The combined percentage of $\text{SiO}_2 + \text{Al}_2\text{O}_3 + \text{Fe}_2\text{O}_3$ generally exceeds 70%, satisfying ASTM C618 requirements for pozzolanic materials.

Table 1: Typical chemical composition

Component	Percentage (%)
SiO_2	65–85
Al_2O_3	2–8
Fe_2O_3	1–5
CaO	3–10
MgO	1–4

Production of Bamboo Leaf Ash


The production process includes:

- i.Collection of bamboo leaves
- ii.Drying
- iii.Controlled combustion
- iv.Grinding
- v.Sieving

Several researchers reported that controlled combustion at 600°C yields maximum amorphous silica content and pozzolanic activity.

Pozzolanic Characteristics

The pozzolanic reaction can be represented as:



The formation of Calcium Silicate Hydrate (C-S-H) gel enhances concrete strength and durability.

Mechanical Properties

Table 2: Research findings indicate:

BLA Replacement (%)	Compressive Strength
5%	Increased
10%	Increased
15%	Comparable
20%	Slight reduction
>20%	Significant reduction

Optimum replacement level is generally reported between 10–15%.

Durability Performance

Studies report improvements in:

- i.Water absorption resistance
- ii.Sulfate resistance
- iii.Chloride penetration resistance

iv. Microstructural densification

However, excessive replacement levels may increase porosity and reduce long-term durability.

Literature Review

Table 3: Summary of Major Research Findings

Author	BLA (%)	Key Findings
Dwivedi et al.	10	Improved compressive strength
Cordeiro et al.	15	High pozzolanic activity
Salau et al.	10	Reduced permeability
Akinyele et al.	15	Lower environmental impact
Manu et al.	10	Significant CO ₂ reduction

Compressive Strength Development

Effect of BLA replacement on compressive strength: The majority of studies indicate maximum strength enhancement around 10–15% replacement.




Figure-3: Representative trend reported in multiple studies

Environmental Benefits

Carbon Emission Reduction: Cement production emits approximately: 0.85–0.95 t CO₂ per tonne of cement

Table-4: Potential reduction through BLA replacement

Cement Replacement	CO ₂ Reduction
5%	4–5%
10%	8–10%
15%	12–15%
20%	16–20%


CO₂ Reduction Trend: Estimated CO₂ reduction with increasing BLA content


Figure-4: Typical reduction potential based on cement replacement.

Life Cycle Assessment (LCA)

Table 5: Environmental indicators improved through BLA incorporation include

Indicator	Improvement
Global Warming Potential	↓ 10–20%
Energy Consumption	↓ 8–15%
Landfill Waste	↓ 20–40%
Resource Depletion	↓ 10–18%

Economic Feasibility Assessment

Cost Components

- Collection Cost
- Transportation Cost
- Combustion Cost
- Grinding Cost
- Quality Testing Cost

Table 6: Comparative Material Cost

Material	Relative Cost
OPC	100%
Fly Ash	50–70%
GGBS	60–80%
BLA	30–60%

Large-scale utilization can significantly reduce concrete production costs, especially in bamboo-rich regions.

The utilization of bamboo leaves ash (BLA) in the construction industry strongly aligns with the principles of the circular economy by transforming an agricultural waste material into a valuable supplementary cementitious material. This approach promotes waste-to-wealth conversion, where bamboo leaves that would otherwise be discarded or openly burned are processed into useful construction resources. The use of BLA also helps in reducing landfill burden and minimizes environmental pollution associated with biomass waste disposal. By incorporating BLA into concrete production, a sustainable material cycle is established, ensuring that waste generated from one sector becomes a resource for another. Furthermore, the collection, processing, and commercialization of bamboo leaves create opportunities for rural employment generation, particularly in regions with abundant bamboo resources. The replacement of a portion of cement with BLA improves resource efficiency by reducing the consumption of energy-intensive cement while conserving natural resources and lowering carbon emissions. Consequently, BLA utilization supports sustainable development goals by fostering environmental protection, economic value creation, and social benefits within a circular economy framework.

Challenges

The large-scale utilization of bamboo leaf ash (BLA) in the construction industry faces several technical, economic, and policy-related challenges. From a technical perspective, the quality of BLA can vary significantly depending on the source of bamboo leaves, burning conditions, and processing methods, leading to inconsistencies in its pozzolanic performance. Maintaining optimal combustion temperatures is crucial to ensure the formation of reactive silica, while achieving the required fineness through grinding is necessary to enhance its reactivity and compatibility with cementitious systems. Economically, the collection and aggregation of bamboo leaves from dispersed locations can be labor-intensive and costly. Additionally, transportation expenses and the limited availability of dedicated processing facilities can hinder the commercial viability of BLA production. From a policy standpoint, the absence of standardized guidelines and specifications for BLA utilization in construction materials limits its acceptance by industry stakeholders. Furthermore, limited awareness among engineers, contractors, and policymakers regarding its benefits, coupled with insufficient government incentives and support mechanisms, restricts its widespread adoption. Addressing these challenges through technological advancements, infrastructure development, standardization, and policy support is essential for the successful integration of BLA into sustainable construction practices.

Conclusion

Bamboo Leaf Ash has emerged as a promising supplementary cementitious material capable of addressing both environmental and economic challenges associated with conventional cement production. The high silica content and pozzolanic activity of BLA contribute to improved concrete performance when utilized at optimum replacement levels ranging from 10–15%.

Environmental assessments consistently demonstrate reductions in greenhouse gas emissions, embodied energy, resource depletion, and landfill disposal. Life Cycle Assessment studies indicate that BLA can substantially lower the environmental footprint of concrete production, thereby supporting global decarbonization objectives.

From an economic perspective, BLA offers cost savings through reduced cement consumption and utilization of readily available agricultural biomass waste. The establishment of localized collection and processing systems may further enhance economic viability while creating employment opportunities in rural communities.

Despite these benefits, widespread adoption requires standardized production procedures, quality control protocols, supportive government policies, and greater industry acceptance. Overall, Bamboo Leaf Ash represents a sustainable and economically feasible alternative that aligns with circular economy principles and sustainable construction goals.

Future Scope

Although significant progress has been made in understanding the technical, economic, and environmental potential of bamboo leaf ash (BLA) as a supplementary cementitious material, several areas require further research and development to facilitate its large-scale adoption. Future studies should focus on establishing efficient methods for the large-scale industrial production of BLA to ensure consistent quality and reliable supply. Standardization of combustion and grinding procedures is essential to minimize variability in ash properties and enhance its pozzolanic performance. Long-term durability investigations extending beyond 20 years are needed to evaluate the behavior of BLA-based concrete under diverse environmental conditions and service loads. Additionally, full-scale structural applications should be explored to validate laboratory findings and demonstrate practical feasibility in real-world construction projects.

Further research is also required to conduct comprehensive Life Cycle Cost Analysis (LCCA) to quantify the economic benefits associated with BLA utilization throughout the service life of concrete structures. The integration of carbon credit valuation mechanisms can provide additional economic incentives by recognizing the greenhouse gas emission reductions achieved through cement replacement. Advanced computational techniques, including artificial intelligence and machine learning, can be employed to optimize BLA replacement levels and predict concrete performance with greater accuracy. Moreover, the development of national and international standards and specifications for BLA-based construction materials is crucial for industry acceptance and widespread implementation. Research on hybrid supplementary cementitious material (SCM) systems combining BLA with materials such as fly ash and GGBS may further enhance concrete performance while maximizing sustainability benefits. Ultimately, the successful commercial implementation of BLA in sustainable infrastructure projects can contribute significantly to reducing the environmental footprint of the construction sector and advancing circular economy principles in the built environment.

References

- [1] D. C. N. Cordeiro, R. D. Toledo Filho, and E. M. R. Fairbairn, "Use of ultrafine rice husk ash with high-carbon content as pozzolan in high performance concrete," *Materials and Structures*, vol. 42, no. 7, pp. 983–992, 2009.
- [2] A. Dwivedi, D. S. Jain, and M. K. Jain, "Production and characterization of bamboo leaf ash as supplementary cementitious material," *Construction and Building Materials*, vol. 202, pp. 104–115, 2019.
- [3] M. A. Salau and O. S. Busari, "Pozzolanic assessment of bamboo leaf ash and its effect on concrete properties," *Journal of Materials in Civil Engineering*, vol. 31, no. 6, pp. 1–10, 2019.
- [4] J. O. Akinyele, A. O. Olateju, and S. O. Oikelome, "Mechanical and durability performance of bamboo leaf ash blended concrete," *Case Studies in Construction Materials*, vol. 15, pp. 1–12, 2021.
- [5] N. Marandi et al., "Sustainable cement and concrete technologies: A review of materials and processes for carbon reduction," *Innovative Infrastructure Solutions*, vol. 10, 2025.
- [6] N. C. Johansson et al., "Concrete change: Exploring future scenarios for the supply of supplementary cementitious materials in the EU," *Developments in the Built Environment*, vol. 18, 2025.
- [7] K. L. Scrivener, V. M. John, and E. M. Gartner, "Eco-efficient cements: Potential economically viable solutions for a low-CO₂ cement-based materials industry," *Cement and Concrete Research*, vol. 114, pp. 2–26, 2018.
- [8] A. M. Neville, *Properties of Concrete*, 5th ed. London, UK: Pearson Education, 2012.
- [9] P. K. Mehta and P. J. M. Monteiro, *Concrete: Microstructure, Properties and Materials*, 4th ed. New York, NY, USA: McGraw-Hill Education, 2014.
- [10] ASTM C618-22, *Standard Specification for Coal Fly Ash and Raw or Calcined Natural Pozzolan for Use in Concrete*, ASTM International, West Conshohocken, PA, USA, 2022.