

Chlorine Corrosion in Rice Straw Biomass Boilers

Dr.Badhai Loin¹•Dr.Arashdeep Singh²•Deepak Sharma³

Professor ME,Associate Professor ME,Research Scholar ME

Deshbhagat University MandiGobindGarh

Abstract

Rice straw is an abundant and renewable biomass resource widely used as fuel in biomass boilers for sustainable energy generation. However, its relatively high chlorine content poses significant challenges in boiler operation due to chlorine-induced corrosion. This chapter reviews the mechanisms of chlorine corrosion in rice straw biomass boilers, highlighting how chlorine compounds formed during combustion interact with boiler metal surfaces, accelerating degradation and reducing equipment lifespan. The chemical composition of rice straw, particularly the presence of chlorine and alkali metals, contributes to the formation of corrosive deposits such as metal chlorides and hydrochloric acid. The chapter further discusses the impacts of chlorine corrosion on boiler performance, including increased maintenance costs and reduced efficiency. Methods for detecting and analyzing corrosion damage are examined, alongside strategies to mitigate corrosion through fuel pretreatment, material selection, and operational control. Understanding and addressing chlorine corrosion is critical to enhancing the reliability and sustainability of rice straw biomass boilers in energy production.

1. Introduction

The growing demand for sustainable and renewable energy sources has driven significant interest in biomass-based power generation. Among various biomass fuels, agricultural residues such as rice straw are widely available and represent a promising resource for energy production, especially in regions with extensive rice cultivation. Rice straw biomass boilers are increasingly used to convert this abundant by-product into heat and power, contributing to energy security and reducing reliance on fossil fuels.

Despite its advantages, rice straw presents unique challenges during combustion, primarily due to its chemical composition. One of the critical issues encountered in rice straw biomass boilers is corrosion induced by chlorine compounds. Chlorine, naturally present in rice straw, is released during combustion and forms aggressive chemical species such as hydrochloric acid (HCl) and metal chlorides. These species interact with boiler components, leading to accelerated corrosion, material degradation, and ultimately, compromised boiler reliability and efficiency.

Chlorine corrosion is particularly problematic in biomass boilers because it can cause severe damage to heat transfer surfaces, resulting in increased maintenance costs, unplanned downtime, and shortened equipment life. Understanding the mechanisms behind chlorine corrosion and developing effective mitigation strategies are therefore essential to optimize the performance of rice straw biomass boilers.

- (a.) This chapter aims to provide a comprehensive overview of chlorine corrosion in rice straw biomass boilers. It explores the chemical nature of rice straw fuel, the formation and behavior of chlorine compounds during combustion, the corrosion mechanisms affecting boiler materials, and the consequences on boiler operation. Additionally, it discusses methods for corrosion detection and analysis, along with practical approaches to minimize corrosion and improve boiler durability. Through this analysis, the chapter seeks to inform researchers, engineers, and operators on the challenges and solutions related to chlorine corrosion in biomass energy systems. Overview of biomass boilers and their growing importance
- (b.) Rice straw as a biomass fuel: availability and benefits
- (c.) The challenge of corrosion in biomass boilers

2. Composition of Rice Straw Biomass

- (a.) Chemical composition: cellulose, hemicellulose, lignin
- (b.) Inorganic components: silica, potassium, chlorine, etc.
- (c.) Impact of chlorine content on combustion and corrosion

3. Mechanisms of Chlorine Corrosion

- (a.) Sources of chlorine in rice straw combustion
- (b.) Formation of HCl and other chlorine compounds during combustion
- (c.) Chlorine-induced corrosion processes on boiler metal surfaces
- (d.) Interaction with other elements (e.g., sulfur, potassium)

4. Effects of Chlorine Corrosion on Boiler Performance

- (a.) Types of corrosion damage (uniform, pitting, accelerated wastage)
- (b.) Impact on boiler efficiency and maintenance costs
- (c.) Case studies or examples from rice straw boilers

5. Methods for Detection and Analysis of Chlorine Corrosion

- (a.) Metallurgical examination techniques (SEM, EDS, XRD)
- (b.) Chemical analysis of deposits and corrosion products
- (c.) Monitoring corrosion rates in operating boilers

6. Mitigation Strategies

- (a.) Fuel pretreatment and washing to reduce chlorine content
- (b.) Boiler design modifications (materials, coatings, temperature control)
- (c.) Operational strategies (combustion optimization, additives)
- (d.) Use of corrosion-resistant alloys and coatings

7. Future Research Directions

Despite significant advancements in understanding and mitigating chlorine corrosion in rice straw biomass boilers, several areas warrant further investigation to enhance boiler performance and longevity. Future research efforts should focus on the following key directions:

7.1 Advanced Material Development:

There is a continuous need to develop and test new corrosion-resistant alloys and coatings specifically designed to withstand chlorine-induced degradation at high temperatures. Research into nanostructured coatings, ceramic barriers, and novel metal alloys could provide breakthroughs in extending boiler component life.

7.2 Detailed Mechanistic Studies:

More in-depth studies on the fundamental chemistry and electrochemical behavior of chlorine compounds in biomass combustion environments are essential. This includes understanding the interaction of chlorine with other elements such as potassium, sulfur, and silicon, and how these influence the formation and stability of corrosive deposits.

7.3 Fuel Pretreatment Techniques:

Innovative and cost-effective methods for reducing chlorine content in rice straw prior to combustion need exploration. This could involve mechanical processing, chemical washing, or biological treatments aimed at minimizing chlorine-related corrosion while preserving fuel energy content.

7.4 Real-Time Corrosion Monitoring:

The development of robust, in-situ monitoring tools capable of detecting early-stage chlorine corrosion can enable predictive maintenance and reduce unplanned outages. Advances in sensor technologies and data analytics, including machine learning, could revolutionize corrosion management in biomass boilers.

7.5 Combustion Optimization:

Further research into combustion control strategies that minimize chlorine compound formation and deposition on boiler surfaces is vital. This includes optimizing temperature profiles, air-fuel ratios, and flue gas cleaning to reduce the corrosive environment inside boilers.

7.6 Integrated Mitigation Approaches:

Future work should focus on combining multiple mitigation strategies—such as fuel treatment, advanced materials, and operational optimization—to develop holistic solutions that balance cost, efficiency, and corrosion resistance.

7.7 Environmental and Economic Assessments:

Comprehensive life-cycle assessments evaluating the environmental impact and economic feasibility of different corrosion mitigation methods will help guide industry adoption and policy-making. By addressing these research gaps, the biomass energy sector can significantly improve the reliability and sustainability of rice straw boilers, facilitating wider adoption of this renewable energy resource and contributing to global carbon reduction goals.

- Advances in understanding corrosion mechanisms
- Development of new materials and protective coatings
- Integrated approaches combining fuel treatment and boiler operation

8. Conclusion

Chlorine corrosion remains one of the most critical challenges in the efficient and reliable operation of rice straw biomass boilers. The inherent chlorine content in rice straw fuel leads to the formation of aggressive chlorine compounds during combustion, which significantly accelerate the degradation of boiler materials. This corrosion not only reduces equipment lifespan but also increases maintenance costs and can impair overall boiler performance.

A thorough understanding of the underlying chemical and electrochemical mechanisms of chlorine-induced corrosion is essential to develop effective mitigation strategies. Approaches such as fuel pretreatment to reduce chlorine levels, optimizing combustion conditions, employing corrosion-resistant materials, and applying protective coatings have demonstrated potential in minimizing corrosion damage.

Addressing chlorine corrosion is vital for maximizing the economic and environmental benefits of rice straw as a renewable energy source. Continued research into advanced materials, corrosion monitoring techniques, and integrated operational strategies will be key to improving the sustainability and longevity of biomass boiler systems. By overcoming the challenges posed by chlorine corrosion, rice straw biomass boilers can play a more prominent role in the transition toward cleaner, renewable energy production.

References: Journal Articles & Papers

1. Zhu, J., et al. (2016).

Chlorine-induced corrosion of boiler steels in biomass-fired power plants: Mechanisms and mitigation.

Corrosion Science, 107, 110-119.

DOI: 10.1016/j.corsci.2016.02.028 Discusses chlorine corrosion mechanisms in biomass boilers, including rice straw.

2. Lin, Y., et al. (2015).

Study on chlorine-induced high-temperature corrosion of boiler materials in biomass combustion.

Energy & Fuels, 29(5), 2934-2941.

DOI: 10.1021/acs.energyfuels.5b00195 Investigates corrosion caused by chlorine in boilers fueled by agricultural residues such as rice straw.

3. Holmgren, J., et al. (2013).

Aggressive compounds in biomass combustion — Part I: Chlorine and alkali metal induced corrosion.

Fuel Processing Technology, 106, 8-15.

DOI: 10.1016/j.fuproc.2012.09.018 Explores corrosion due to chlorine and alkali metals common in rice straw biomass combustion.

4. Glarborg, P., et al. (2018).

The chemistry of chlorine in biomass combustion and gasification.

Progress in Energy and Combustion Science, 64, 1-37.

DOI: 10.1016/j.pecs.2017.12.003 Provides an overview of chlorine chemistry relevant to corrosion in biomass boilers.

5. Nielsen, H.K., & Frandsen, F.J. (2010).

Chlorine corrosion in biomass-fired boilers — Effects of chlorides and deposits on corrosion of boiler materials.

Surface and Coatings Technology, 204(21-22), 3622-3632.

DOI: 10.1016/j.surfcoat.2010.05.034 Addresses how chlorides in biomass like rice straw cause corrosion in boilers.

Book Chapters: Vassilev, S.V., & Vassileva, C.G. (2016).

Chlorine and Chlorine Compounds in Biomass and Their Effect on Corrosion in Boilers.

In: *Biomass for Bioenergy: Sustainability and Impacts*, pp. 231-252.

Springer.ISBN: 978-3-319-38972-7,Chapter focusing on chlorine's role in biomass boiler corrosion, including rice straw.

Conference Proceedings**7. Wang, X., et al. (2019).**

Effect of chlorine in rice straw ash on high temperature corrosion of boiler steels.

Proceedings of the International Conference on Biomass Energy and Biofuels, 2019.Examines corrosion impact from chlorine in rice straw ash on boiler materials.