

COMPREHENSIVE ANALYSIS OF WIND TURBINE BLADE DAMAGE

Mr. SHYAM SUKHADEO SORMARE ¹

MECHANICAL ENGINEERING

ANJUMAN COLLEGE OF ENGINEERING AND TECHNOLOGY,

NAGPUR, MAHARASHTRA, INDIA

-----***-----

Abstract - This article aims to review the potential causes that can lead to wind turbine blade failures, assess their significance to a turbine's performance and secure operation, and summarize the techniques proposed to prevent these failures and eliminate their consequences. Various factors such as lightning, fatigue loads, icing accumulation, and leading-edge erosion from airborne particulates can contribute to damage in wind turbine blades, ranging from minor surface erosion to complete blade destruction. The severity of these effects is highly dependent on the surrounding environment and climate conditions. Therefore, selecting an installation site with favorable conditions is the most effective measure to minimize the possibility of blade damage. However, several techniques and methods have been applied or are being developed to prevent blade damage, with the aim of reducing the risk, if not eliminating it entirely. The combined application of damage prevention strategies with a Supervisory Control and Data Acquisition (SCADA) system is considered the optimal approach for effective treatment. By comprehensively reviewing the causes of wind turbine blade failures and the associated prevention techniques, this article provides valuable insights for researchers, industry professionals, and stakeholders involved in wind energy generation. The findings emphasize the significance of proactive measures to minimize blade damage, ensuring the efficient and secure operation of wind turbines.

Key Words – Wind Turbine, Lighting failure, Fatigue, Coating & Surface treatment, Inspection & maintenance, SCADA system.

1. INTRODUCTION

The scope of this article is to fill this gap by providing a comprehensive review of potential causes of wind turbine blade failures, their impact on turbine performance, and the techniques used to prevent or remedy such failures.

The article presents the potential causes of wind turbine blade failures and discusses the severity of the damage induced by these causes. Factors such as strong storm winds, rain, hail, lightning, repeated wind loads, and shear effects are explained as sources of structural damage to wind turbine blades. The economic impacts of blade damage, including the shutdown of turbines for repair and the cost of repair itself, are also highlighted. The article emphasizes that wind turbine blades are particularly susceptible to damage due to their exposure to the environment and the large size and weight of the blades.

The article focuses on the methods and techniques proposed or implemented to prevent or remedy the most common types of blade damage. These methods are described in detail, drawing from both applied research and practical experience gained from the inspection of wind parks under severe weather conditions. The article mentions that while there are numerous studies on specific types of blade damage and corresponding remedies, there is a lack of comprehensive articles that gather and present this information in a comprehensive manner. The article also references some specific works that have proposed novel techniques for detecting wind turbine blade damage, such as hierarchical identification frameworks using machine learning algorithms, artificial intelligence and neural networks, strain measurement, acoustic emission, ultrasound, vibration, thermography, and machine vision. Non-destructive testing methods for wind turbine blades, including visual testing, ultrasonic testing, thermography, radiographic testing, electromagnetic testing, acoustic emission, and stereography, are also discussed.

Furthermore, the article mentions a few studies that have introduced probabilistic models and decision-making approaches to optimize inspection intervals and maintenance strategies for wind turbine blades. It also highlights a review of fault diagnosis, prognosis, and control methods for wind turbine systems, including blade-related issues.

In conclusion, this article aims to provide a comprehensive review of the potential causes of wind turbine blade failures, their impact on turbine performance, and the techniques used to prevent or remedy such failures. It fills a gap in the literature by presenting a consolidated overview of the most common types of blade damage and the prevailing preventive or remedial measures proposed so far.




Figure 1: Damaged Turbine Wind Blade

2. Causes of Wind Turbine Blade Failures

The wind turbine is a complex structure. Although there is no single approach and there is variability in the commercial designs, a typical WTB is a thin-walled multi-cellular hollow airfoil-shaped cross-section. For its manufacture, a number of materials and material systems are used for structural purposes (fibre composites and sandwich composite systems) as well as aesthetic purposes (primers, UV gel coats, paint, etc.). Typical construction layouts of wind turbine blades are presented. The potential causes of wind turbine blade failures can be classified into the following four categories

1. Damage from lightning;
2. Failures due to fatigue;
3. Leading edge erosion;
4. Damage from icing.

The types of damage caused to wind turbine blades—originating from the above four different sources—along with their significance to the turbine's performance and secure operation, are detailed in the following sub-sections.

2.1 Damage from Lightning:

Lightning strikes can pose a significant threat to wind turbine blades. When a lightning strike occurs, it can cause structural damage and weaken the blade material. This can lead to cracks, delamination, and internal damage within the blade. Lightning strikes can also damage the electrical systems of the turbine, including the generator and control systems. Proper grounding and lightning protection systems are implemented to minimize the risk of damage from lightning strikes.

the significant impact of lightning on wind turbine blades and the frequency of lightning-related damage. Here are some key points

- Lightning outages in Europe ranged from 3.9% to 8.0% between 1991 and 1998, while in Japan, the figure was around 10-20% from 2002 to 2006.
- Field observations indicate that wind turbines experience a significant number of lightning strikes during their lifetime.
- Lightning strikes predominantly occur within the outermost 1 meter of the blade tip, but there is an increasing risk of inboard puncture as well.
- Current lightning air-termination systems for rotor blades can withstand about 98% of lightning strikes, but there is still a risk of local damage, particularly at the attachment point.
- Damage from lightning to wind turbine blades depends on the structural materials used. PVC and PET can suffer pyrolysis and cracks, while balsa wood blades may experience fibred breakage and delamination.
- The most common types of damage caused by lightning strikes are delamination, debonding, shell detachment, and tip detachment.
- Delamination occurs when the pressure and temperature generated by lightning cause the piles of laminate to detach from each other.
- Debonding refers to the separation of the upper and lower shells of the blade, usually caused by the expansion of air and vaporization of trapped moisture inside the blade.
- Shell detachment involves several meters of one or both shells becoming completely detached from the load-carrying structure, usually starting with shell debonding.
- Tip detachment is the complete detachment of several meters of the blade tip from the rest of the blade, which can be considered the most critical type of damage caused by lightning strikes.
- On average, each wind turbine can expect blade damage due to lightning approximately every 8.4 years, with 2-3 lightning strikes capable of causing damage over a 20-year period.
- The repair process for lightning damage can vary depending on the severity, ranging from a few hours for minor delamination to several days for detachment.

Overall, lightning damage to wind turbine blades not only incurs repair costs but also results in lost income due to turbine downtime during repairs. Understanding the types of damage caused by lightning is crucial for developing effective strategies to mitigate these risks and ensure the reliability and performance of wind turbines.



Figure 2: Damaged Turbine Wind Blade due to lightning

2.2 Failure due to fatigue

Wind turbine blades are subjected to dynamic loading conditions caused by wind gusts, turbulence, and rotational forces. Over time, these cyclic loads can lead to fatigue damage in the blade structure. Fatigue failures typically start as small cracks or defects and gradually propagate under repeated loading cycles. If not detected and repaired in time, these cracks can grow and eventually lead to catastrophic blade failure. Regular inspections, monitoring, and maintenance practices are essential to identify and address fatigue-related issues. Moisture is an important environmental parameter that can contribute to fatigue damage in wind turbine blades. Despite the water insulation of glass fiber reinforced polyester (GFRP) blades, moisture can still penetrate the inner material of the blades. The connection between the blade and the turbine's hub, which uses a bolted joint, is particularly susceptible to fatigue damage as it bears the mechanical loads transferred and gathered at that point. The major effects of absorbed moisture on the laminates of the blades are as follows:

- Reduction of the glass transition temperature of the matrix resin.
- Damage to the interface between the fibers and the resin.
- Reduction of the cure-induced residual stresses through swelling, which may retard failure.

- Ice formation in wind park installations in subzero temperatures, which can act as a wedge between the plies and lead to delamination propagation.

When a composite material is subjected to water and fatigue loads, it exhibits increasing matrix cracking, which accelerates water penetration. However, the precise effects of moisture absorption on the mechanical properties of GFRP blades are not accurately known.

While moisture is one environmental factor that can contribute to fatigue damage, the primary cause of fatigue damage is the development of loads from fluctuating forces. Wind is the main source of such forces, especially in turbulent wind conditions. The land morphology and obstructions around a wind turbine can significantly affect the wind flow, leading to turbulent wind conditions and wind shear. This varying wind environment exposes the turbine's structure to adverse fatigue conditions.

Wind turbine blades, which experience repeated bending, are the most vulnerable components to fatigue damage due to fluctuating forces. The blade joints with the turbine's hub are the most likely places for fatigue damage to appear, regardless of the source of the fatigue conditions. Factors such as stress concentration, bolt holes, built-in stresses, offsets, changes of section, and the use of different materials contribute to fatigue damage in this area.

The response of composite materials to fluctuating loads follows three stages of fatigue damage accumulation over time: an initial load period with minor damage formation, a longer period of increasing damage linearly with time, and, if stress is sufficiently high, a third stage characterized by severe damage leading to failure. The trailing edge adhesive joint, due to its complex geometry, manufacturing technique, and operating conditions, is also susceptible to damage from the shear effect.

The economic impact of fatigue damage and the need for repairs can be significant. Manufacturing three blades for a wind turbine accounts for 15-20% of the total manufacturing cost. The complete replacement of a destroyed blade can cost up to USD 200,000, and the use of a crane for repairs can add an additional cost of USD 350,000 per week. The repair process for a severely damaged turbine blade can take several days, causing income loss. Each day that a wind turbine remains inoperative results in income losses ranging from USD 800 to 1600, depending on the available wind potential. Therefore, it is crucial to employ non-destructive and cost-effective techniques for timely detection of potential failures in the blades' structural integrity due to fatigue loads



Figure 3: Damaged Turbine Wind Blade due to Fatigue

2.3 Leading Edge Erosion

Wind turbine blades are exposed to various environmental factors, including wind, rain, sand, and dust. Over time, these elements can cause erosion and degradation of the blade's leading edge. Leading edge erosion occurs when the protective coating or material on the front edge of the blade wears off or becomes damaged. This erosion can reduce the aerodynamic performance of the blade, leading to decreased power output. Regular maintenance and repair of the leading-edge coating is necessary to prevent significant erosion. Leading edge erosion of wind turbine blades is primarily caused by exposure to airborne particulates, such as rain, hailstone, sea spray, dust, sand, as well as UV light and humidity/moisture. This exposure gradually increases the surface roughness of the blade, resulting in higher friction drag and aerodynamic loss. The aerodynamic performance of the blade is negatively impacted, leading to reduced lift and increased drag, especially as erosion levels become more severe. In extreme cases, leading edge erosion can even affect the structural integrity of the blade.

The severity of leading-edge erosion is site-dependent and varies based on the environmental conditions. In arid and sandy climates, sand and dust particles can cause erosion, while wetter habitats may have different challenges. Near-shore locations may also face significant erosion from sand. Raindrops can contribute to erosion, with their kinetic energy, diameter, temperature, and sea salt content being critical factors.

Careful handling of the blade during manufacturing, transport, and installation is important to prevent small tears or scratches that can initiate further wear and erosion.

To estimate the forces exerted on the blade's coating by airborne particles, let's consider the example of a raindrop traveling with the wind. Assuming a raindrop diameter of 3 mm (about 0.12 in) and a terminal

velocity of 8 m/s, when the raindrop strikes a rotating blade with a 90 m/s tangential tip speed, the impact velocity between the raindrop and blade can be around 80 m/s. The resulting force of impact between the raindrop and the blade is calculated to be approximately 76 N.

Hailstones can cause even more severe effects on a blade's coating due to their larger diameters. The average size of hailstones varies based on the location, and on-site measurements are necessary for accurate estimations. Larger hailstones have increased mass, kinetic energy, and terminal velocity, which can result in higher impact forces on the blade's coating. The forces exerted by hailstones can range from 1.7 kN to 6.9 kN at the blade tip, depending on the hailstone diameter.

Seawater spray is another factor that can contribute to leading edge erosion, particularly for offshore or near-shore wind turbines. Apart from exerting forces and pressures similar to raindrops, the sea salt crystals transported in the spray can accumulate on the blade's leading edge, leading to degradation of aerodynamic performance and potential corrosive damage.

Leading edge erosion directly affects the income generated by wind turbines due to the degradation of aerodynamic performance. Repair costs are not significant if the damage is detected early, and appropriate repairs are carried out in a timely manner.



Figure4: Damaged Turbine Wind Blade due to Edge Erosion

2.4 Damage from Icing:

In colder climates, wind turbine blades are susceptible to icing, especially during winter months. Ice accumulation on the blades can add substantial weight and alter the aerodynamic balance of the rotor. This imbalance can cause increased stress on the blades and the entire turbine structure. Additionally, as the ice melts and freezes, it can lead to the formation of ice dams, which further impacts the blade's performance. De-icing systems or other measures, such as heating elements or specialized coatings, are often employed to prevent or remove ice buildup and minimize the associated damage. Atmospheric icing can have significant

impacts on structures exposed to the atmosphere, such as wind turbines. There are two main types of atmospheric icing: in-cloud icing (rime ice or glaze) and precipitation icing (freezing rain or drizzle, wet snow). Here's a breakdown of each type:

Rime ice: Rime ice is formed when supercooled liquid water droplets in clouds or fog freeze upon contact with a surface. Small droplets result in the formation of soft rime, which is a fragile, snow-like ice formation consisting of thin ice needles or flakes. Large droplets lead to the formation of hard rime, which is opaque and adheres firmly to surfaces.

Glaze: Glaze is formed by freezing rain or wet in-cloud icing. It results in the formation of a smooth, transparent, and homogenous ice layer that strongly adheres to surfaces. Glaze is typically formed at temperatures ranging from 0 °C to -6 °C.

Wet snow: Wet snow is formed when partially melted snow crystals with high liquid water content adhere to surfaces. It has increased cohesive forces and can stick to objects. Wet snow accretion occurs at temperatures between 0 °C and +3 °C.

Icing events progress through several stages:

Meteorological icing: This is the period when meteorological conditions favor ice formation. It includes factors such as temperature, humidity, and wind speed.

Instrumental icing: Once ice has formed on a structure, this period represents the time during which the ice remains. Wind turbines may experience operational issues and performance degradation during this stage.

Incubation time: This is the delay period between the start of meteorological icing and the start of instrumental icing. The length of the incubation time depends on the surface and the temperature of the structure.

During the icing process, wind turbines are subjected to different phases, and the accumulation of ice on the blades can lead to various problems. These include reduced aerodynamic efficiency, decreased power production, increased vibrations and noise, imbalances in the blades, errors in wind measurements, and the risk of ice throwing. Icing can cause fatigue loads, structural wear, and potential safety hazards.

The cost associated with icing mainly refers to income loss due to lower aerodynamic performance or the interruption of wind turbine operation. The reduction in annual electricity production can exceed 10% due to icing, and in extreme cases with extended shutdowns, it can be higher than 20%, resulting in significant income loss. I hope this information provides a comprehensive understanding of atmospheric icing and its

impact on wind turbines. It's worth noting that these potential causes of wind turbine blade failures are not mutually exclusive, and a combination of factors can contribute to blade damage and failure. Proper design, material selection, maintenance, and monitoring systems are essential for mitigating these risks and ensuring the safe and efficient operation of wind turbines.



Figure5: Damaged Turbine Wind Blade due to Icing

3. Significance of Blade Damage to Performance and Operation

Blade damage to wind turbines can have significant implications for performance, operation, structural integrity, safety, and the surrounding environment. Here are the key points to consider:

3.1 Effects on power generation efficiency: Blade damage, such as erosion, leading-edge erosion, or surface roughness, can decrease the aerodynamic efficiency of the blades. This results in reduced power output as the turbine is less effective at capturing wind energy. Over time, the accumulated effects of blade damage can lead to a decline in the overall performance of the wind turbine.


3.2 Impact on structural integrity and safety: Blade damage can compromise the structural integrity of the turbine, leading to safety concerns. Damage such as cracks, delamination, or lightning strikes can weaken the blades and increase the risk of failure, which may result in catastrophic blade failure or detachment. This poses a safety hazard not only to the turbine itself but also to nearby structures, personnel, and the environment.

3.3 Environmental and climate conditions: The environmental and climate conditions at a wind turbine site can contribute to blade damage severity. Factors such as wind speed, direction, turbulence, temperature, humidity, and the presence of airborne particles or corrosive agents can influence the rate and type of damage experienced by the blades. For example, coastal areas with high salt content in the air may increase the risk of corrosion, while regions with high wind speeds and turbulence may subject the blades to higher stresses and fatigue.

3.4 Influence on blade damage severity: The severity of blade damage is influenced by various factors. These include the design and materials of the blades, the quality of manufacturing and maintenance, the operational conditions of the turbine, and the frequency and effectiveness of inspections and repairs. Proper maintenance practices and proactive monitoring can help detect and address blade damage early, mitigating the potential for more severe consequences.

3.5 Importance of site selection and its impact: Site selection plays a crucial role in mitigating blade damage risks. Factors such as wind conditions, environmental factors, and terrain characteristics need to be carefully considered during the site selection process. Choosing a location with favorable wind conditions, minimal turbulence, and low exposure to corrosive agents can help reduce the likelihood and severity of blade damage. Adequate spacing between turbines and consideration of potential obstructions can also minimize the impact of wake effects and turbulence on neighboring turbines.

Overall, blade damage affects both the performance and safety of wind turbines. Considering environmental and climate conditions, implementing proper maintenance practices, and selecting suitable turbine sites are essential to optimize turbine performance, ensure structural integrity, and reduce the risks associated with blade damage.



4. Prevention techniques for blade damage

Prevention techniques for blade damage in wind turbines include various measures and strategies. Here are some specific techniques that can help prevent blade damage:

4.1 Lightning Protection Systems:

Installing lightning protection systems is essential to mitigate the risk of lightning strikes, which can cause significant damage to wind turbine blades. Lightning rods or receptors are typically mounted on the blades and connected to a grounding system. These systems help divert the electrical charge from lightning strikes safely to the ground, protecting the blades from direct strikes and reducing the risk of damage. Protection from lightning damage is crucial for wind turbines, especially as the size of modern turbines increases. Lightning strikes can cause significant damage to wind turbine blades, resulting in higher repair costs. Additionally, failure to ensure adequate lightning protection can negatively impact public perception of wind energy.

There are several approaches to lightning protection for wind turbines, including:

- **Adequate driving of the lightning strike:** This involves directing the lightning strike to a preferred point, such as the blade's air termination system. The goal is to provide a path of least resistance for the lightning current to follow.
- **Installation of appropriate grounding:** Ensuring proper grounding is essential to allow the lightning current to safely pass through the turbine's structure into the ground without causing damage. This helps protect against strong electric or magnetic fields.
- **Minimization of voltage gradients:** Efforts should be made to reduce voltage gradients developed in and around the wind turbine. High voltage differentials can increase the likelihood of lightning strikes and subsequent damage.

The IEC 61400-24 standard defines the prerequisites and requirements for blade lightning protection systems (LPS). Different types of lightning protection systems can be installed in wind turbine blades, including air termination systems, high resistive tapes and diverters, down conductors inside the blade, and conducting materials for the blade surface.

While these protection measures can reduce the probability of lightning damage, no method can guarantee absolute protection against lightning strikes. The use of lightning receptors, such as metal receptors located at the blade's tip, is a common technique but cannot provide complete protection. Other approaches, such as

isolated lightning towers or non-metallic mesh construction on the blade's surface, have been explored but may not be practical or economically feasible in all cases. It's important for wind turbine manufacturers and operators to follow industry standards and guidelines for lightning protection and regularly assess and update their protection systems to enhance safety and minimize damage from lightning strikes.




Figure7: Lightning protection methods for wind turbine Blades

5.2 Load Monitoring and Control Systems:

Load monitoring and control systems continuously monitor the loads acting on the wind turbine blades. By collecting real-time data on parameters such as blade vibration, strain, and wind conditions, these systems enable operators to optimize the turbine's operation and adjust its settings to minimize stress and fatigue on the blades. This helps prevent excessive loads that can lead to damage and failures. To prevent damage to wind turbine blades caused by fatigue, two approaches can be taken: predicting the blade's material behaviors and structural properties in relation to fatigue and selecting an appropriate installation site for the wind park.

Blade Material Behavior Prediction: Predicting the dynamic behavior of wind turbine blades is essential in the design and development process. This prediction affects the turbine's efficiency and electricity production, as well as the structural approach to the turbine's construction. Various methods of analysis can be employed, considering both the blade's geometry and material properties.

Proper Siting of Wind Turbines: The siting of wind turbines plays a crucial role in minimizing fluctuating aerodynamic loading and fatigue consequences. It is recommended to avoid areas with small particles of soil or dust and areas with intensive changes on mountain slopes and steep cliffs. Generally, wind load variations are less intense in milder land terrain.

Turbulence intensity is also a factor that can affect the life-to-failure of wind turbine blades. By collecting data from wind measurement campaigns or wind models, the best location with minimal fatigue damage can

be determined. After installation, regular and valid inspection of wind turbine operations is important to detect potential fatigue-induced damage. Timely detection allows for easier and more cost-effective repairs.

Inspection of wind turbine blades is a complex task due to their curved surface, multi-layered structures, anisotropic materials, and variable thicknesses. Non-destructive testing (NDT) or non-destructive evaluation (NDE) methods are commonly used for monitoring blades. The following NDT techniques are often applied:

- **Visual Testing:** Visual inspection is used to identify cracks and discontinuities on blade surfaces. Unmanned aerial vehicles (UAVs) equipped with cameras can provide images for inspection, even in isolated and difficult-to-access locations. Artificial intelligence methods are employed to interpret the captured images and detect faults.
- **Ultrasonic Testing:** Ultrasonic evaluation is widely used to detect delamination, adhesive defects, and resin-poor areas. Mathematical and artificial intelligence methods help overcome noise introduced by composite materials and complex geometry. Wavelet transform, pattern recognition, guided wave analysis, and harmonic motion analysis are some of the techniques used.
- **Thermography:** Infrared thermography detects variations in thermodynamic properties and surface temperature patterns. It can quickly identify hot spots caused by component degeneration or poor internal contact. Appropriate filters can be applied to isolate noise generated by this method.
- **Radiographic Testing:** Radiographic testing utilizes X-rays to measure variations in density caused by changes in material properties or internal delamination. Advanced digital tomography technology enables 3D visualization of the blade's structure.
- **Acoustic Emission:** Acoustic emission relies on the propagation of elastic waves through the material. Abnormalities in wave propagation and frequency indicate failures such as cracks, discontinuities, delamination, and breakage. Piezoelectric sensors installed on the blade's surface detect acoustic events. Data processing techniques, such as neural networks, Gaussian mixture models, and wavelet transforms, are used to analyze the collected data.

Implementing these non-destructive testing methods allows for effective inspection and early detection of faults or damage in wind turbine blades, enabling timely repairs and maintenance...




Figure8: Indicative allocation of Piezoelectric sensors for detection of stress, fatigue and many more.

5.3 Anti-Icing and De-Icing Methods:

To prevent ice accumulation on wind turbine blades, anti-icing and de-icing methods can be employed. Anti-icing techniques aim to prevent ice formation by heating the blades or applying anti-icing coatings that inhibit ice adhesion. De-icing methods, such as mechanical devices or heating systems, are used to remove ice once it has formed. These methods help maintain the aerodynamic efficiency of the blades and prevent excessive loads caused by ice accretion. Protection against icing on wind turbine blades is an important consideration to ensure their optimal performance and safety. There are two main approaches to address icing: de-icing and anti-icing techniques.

De-icing techniques involve the removal of ice from the blades. The goal is to minimize the recovery time after an icing event. One widely used de-icing method is the hot air heating system. In this system, hot air generated by electric resistance is circulated inside the blade, increasing its temperature and melting the ice or snow. The hot air is propelled by a fan located in the root of the rotor blade and circulated throughout the blade's length. This system has been tested and implemented by manufacturers like ENERCON, with satisfactory results. However, one potential drawback is the high temperature induced in the blade's interior, which may pose a risk to the structural integrity of composite blades. Control systems for de-icing rely on

ice detectors and blade surface temperature sensors, and algorithms are developed to optimize the timing of activation and deactivation of the de-icing system.

On the other hand, anti-icing techniques aim to prevent or delay ice build-up on the blades. Coatings with hydrophobic properties are commonly used as passive anti-ice surfaces. These coatings prevent water from remaining on the surface, reducing ice formation. However, no general hydrophobic coating has been reported to exhibit outstanding anti-icing results due to the complex factors affecting ice formation. Another approach involves the use of biochemical technologies inspired by organisms in polar climates. These technologies incorporate substances with antifreeze properties into surface coatings, causing freezing point depression and preventing ice formation. Additionally, coatings with hydrophilic centers in a hydrophobic environment allow water molecules to adhere to specific positions on the blade surface, facilitating the removal of ice crystals.

Some innovative approaches involve the use of ultrasonic-guided waves (UGW) to remove ice. UGW propagates along the length of the blade and can induce displacements and stresses inside the material, effectively removing ice. However, these methods are still in the research and development phase.

When considering the effects on public safety and health, wind turbine operations with iced-up blades may be restricted in certain countries, especially for glazed ice conditions which are considered more dangerous. Visibility can be significantly reduced under active icing conditions, so warning signs and visual alerts are important to ensure public safety. The cost associated with installing and applying anti-icing or de-icing systems can be up to 5% of the total procurement cost of a wind turbine.

Overall, while some de-icing and anti-icing techniques are commercially available and have been tested, many are still under development or in the early stages of field testing. Continued research and innovation in this area are necessary to improve the efficiency and effectiveness of icing protection systems for wind turbines.

5.4 Coatings and Surface Treatments:

Applying specialized coatings and surface treatments to wind turbine blades can enhance their durability and resistance to environmental factors. Protective coatings can provide corrosion resistance, UV protection, and erosion resistance. Surface treatments, such as leading-edge erosion protection systems, can help mitigate

damage caused by rain, sand, or other particles impacting the blades during operation. Protection against leading edge erosion on wind turbine blades can be achieved through various techniques and coatings:

1. **Polyurethane Coatings:** Applying a polyurethane coating on the blade leading edges is a commonly used technique for erosion protection. Polyurethane is a segmented material with both hard and soft segments, providing a combination of stiffness, hardness, toughness, and damping properties.
2. **Multilayer Coatings:** Multilayer protective coatings involve combinations of different materials to enhance strength and anticorrosive properties. This can include hybrid technologies, polymer-metal laminates, or the introduction of alloys into the main erosion protection material. The use of electroformed nickel shields in outer blade regions and thermoplastic coatings in intermediate regions is another approach.
3. **Particle-Reinforced Coatings:** Enhancing polymer coatings with microscale and nanoscale particle reinforcements improves their erosion protection capabilities. Surface-treated ceramic nanoparticles or graphene-based coatings have been proposed for this purpose, but their effectiveness depends on various factors such as manufacturing, nanoparticle distribution, and surface processing.
4. **Interpenetrated Polymers:** Interpenetrated polymers based on polyurethane and epoxy resins offer attractive features like higher strength and improved damping properties. The addition of graphene to the polymer network has been suggested for further enhancement.
5. **Auxetic Structures:** Auxetic structures, which exhibit a negative Poisson's ratio behavior, can improve damping properties. Chiral structures and star-shaped bi phase cells are examples of designs that dissipate energy in wind turbine blades' edgewise/shear modes, reducing erosion.

Careful handling of the blades during manufacturing, transport, and installation is crucial to avoid small tears or scratches that can act as initiation sites for wear and erosion. Surface roughness plays a role, as smoother coatings tend to have less favorable conditions for leading edge erosion. However, some research suggests that rough surfaces inspired by the shells and skins of desert animals can exhibit improved anti-corrosion performance. Bio-inspired anti-corrosive rough surfaces incorporating features from desert scorpions have been developed.

Overall, a combination of appropriate coatings, materials, and handling practices helps protect wind turbine blades against leading edge erosion, extending their operational lifespan.



Figure9: Application of anti- corrosion coating on wind turbine blade leading edge

5.5. Inspection and Maintenance Protocols:

Implementing regular inspection and maintenance protocols is crucial for detecting and addressing any potential blade damage or deterioration. Visual inspections, non-destructive testing methods, and monitoring systems should be utilized to identify early signs of damage, such as cracks, delamination, or erosion. Timely repairs and maintenance should be carried out to prevent further degradation and ensure the integrity of the blades.

Operating strategies for wind turbines aim to detect damage early and take appropriate actions to prevent severe damage that could affect their operations and increase repair costs. These strategies rely on collecting measurements of critical parameters such as temperature, noise, rotational speed, etc., using instruments like sensors and cameras for optical inspection. Modern wind turbines are equipped with automatic inspection and control systems that detect malfunctions or failures in various components of the turbine, including the nacelle, bearing structure, and rotor. Historical data and weather data are also taken into account. Once the measurements and data have been gathered and a fault is detected, operating algorithms are applied to optimize the turbine's operation. The specific algorithms depend on the severity of the damage. The primary objectives are to prevent further degradation of the turbine's operational status, protect its structural integrity, and minimize electricity production losses. These algorithms are often developed based on mathematical models or the experience gained from similar technical facilities operating under similar conditions. For example, Monte Carlo simulations can be used to predict blade deterioration, and data from offshore oil pumping stations can inform operating strategies for offshore wind parks.

The potential decisions that can be made based on the operating algorithms include:

- Shutdown of the wind turbine in case of severe damage or adverse weather conditions that may exacerbate the damage.
- Selective shutdown or reduced operation of one or more wind turbines if their wake affects the operation of the damaged turbine.
- Controlled operation of the damaged wind turbine to minimize power production loss while simultaneously executing the repair process.

These strategies aim to balance the need for a continued operation to generate electricity with the requirement to ensure the turbine's safety and minimize further damage. By implementing appropriate operating strategies, wind turbine operators can optimize the performance, maintenance, and repair of their turbines. By incorporating these prevention techniques into wind turbine operations, operators can minimize the risk of blade damage, improve performance and reliability, and extend the lifespan of wind turbine blades. It is important to develop a comprehensive maintenance and monitoring program tailored to the specific environmental conditions and challenges at each wind farm site.

6. Integration of Prevention Strategies with SCADA Systems

Integrating prevention techniques with SCADA (Supervisory Control and Data Acquisition) systems offers several benefits for wind turbine blade damage mitigation. Here are some advantages of combining prevention strategies with SCADA systems:

- **Real-time Monitoring:** SCADA systems enable real-time monitoring of critical parameters such as temperature, noise, rotational speed, vibration, and other relevant data. This allows for continuous surveillance of the wind turbine's condition and early detection of potential issues that may lead to blade damage. Real-time monitoring ensures prompt response and timely intervention.
- **Early Detection:** By collecting data from various sensors and instruments installed on the wind turbine, SCADA systems can identify anomalies or deviations from normal operating conditions. This early detection of abnormal behavior or performance variations can indicate potential blade damage or malfunction. Detecting problems at an early stage allows for proactive measures to prevent further degradation or severe damage.
- **Rapid Response:** SCADA systems provide a means for immediate response to detected issues. When anomalies or deviations are identified, the system can trigger alarms or notifications to alert operators or maintenance personnel. This enables swift action to be taken, such as shutting down the turbine,

implementing controlled operation, or initiating repair processes to mitigate damage and minimize production losses.

- **Data Analysis and Trend Monitoring:** SCADA systems collect and store large amounts of historical data from wind turbine operations. By analyzing this data and monitoring trends, patterns, and performance metrics, operators can identify potential risks or vulnerabilities that may lead to blade damage. Such insights can help in optimizing maintenance schedules, identifying recurring issues, and implementing preventive measures to reduce the likelihood of blade damage.
- **Enhanced Decision-Making:** The integration of prevention techniques with SCADA systems provides operators with comprehensive and real-time information about the wind turbine's condition. This enables data-driven decision-making regarding operational adjustments, maintenance prioritization, and repair strategies. By having a holistic view of the turbine's health and performance, operators can make informed decisions to optimize operations and minimize downtime.
- **Cost Savings:** The combination of prevention techniques and SCADA systems can lead to cost savings by reducing repair costs, minimizing production losses, and extending the operational lifespan of wind turbine blades. Early detection and timely response to potential blade damage can prevent the escalation of issues, reducing the need for costly repairs or blade replacements. Additionally, by minimizing production losses through prompt intervention, the economic efficiency of the wind project is improved.

In summary, integrating prevention strategies with SCADA systems in wind turbine operations offers real-time monitoring, early detection, rapid response capabilities, data analysis, enhanced decision-making, and cost savings. This integration enhances the overall reliability, performance, and economic viability of wind turbines by mitigating blade damage risks and optimizing maintenance and repair processes.

7. Conclusion

In conclusion, this article provides a comprehensive analysis of potential causes of wind turbine blade damage and the methods available to prevent or remedy them. The following key conclusions can be drawn based on the inspections, results, and statistical data presented:

The surrounding environment and weather conditions play a significant role in wind turbine blade damage. Proper selection of the installation site and appropriate turbine siting can help minimize induced fatigue loads. Mild weather conditions can also reduce the probability of damage from lightning, icing, and leading-edge erosion.

While various techniques and approaches contribute to the reduction of damage risk, there is no foolproof method for guaranteed protection against all potential damage. Each method helps mitigate the risk but cannot eliminate it entirely.

A SCADA (supervisory control and data acquisition) system can be valuable for operation and maintenance in adverse climates. It aids in ice detection, lightning damage assessment, and vibration monitoring. The system collects important information such as ambient temperature, visibility, rotor blade photos, wind sensors, and rotor speed. Early detection of damage through the supervisory system minimizes the impact on turbine operation and reduces repair costs.

Lightning can cause the most severe damage, even leading to total blade destruction. Fatigue loads, accumulated over time, can also cause significant damage. However, the impact of fatigue loads can be prevented through proper inspections, whereas lightning damage is challenging to prevent or control once it occurs.

Icing, although not structurally destructive to the blade, can significantly reduce wind turbine performance over prolonged periods. This can have a negative economic impact on the project, comparable to or even higher than the cost of repairing a lightning-struck blade.

Leading edge erosion is a milder form of damage, affecting only the outer coating of the blade and not posing a risk to its structure. Timely detection allows for easy repairs.

All forms of blade damage can have a substantial impact on the wind turbine's aerodynamic performance and annual electricity production. Icing can lead to production reductions exceeding 10% and potentially reaching 30%. Leading edge erosion increases drag coefficient, causing a 5% reduction in annual electricity production. Lightning and fatigue can result in significant production losses when turbine shutdowns are required for maintenance or repair, or in the worst-case scenario, when a blade is destroyed.

The cost of wind turbine blade repairs depends on the severity of the damage. Repairing a lightning-damaged blade can cost up to USD 30,000, while replacing a destroyed blade can reach USD 200,000. Blades account for 15% to 20% of the total manufacturing cost of a wind turbine. Each day of inoperability due to blade damage results in income losses ranging from USD 800 to USD 1600, depending on the wind potential available. These figures underscore the significance of wind turbine blade damage on wind park performance and the economic efficiency of the project.

Overall, understanding the causes of blade damage and implementing effective prevention and repair strategies is crucial for optimizing wind turbine performance, reducing downtime, and maximizing economic returns.

8. References:

- World Wind Energy Association (WWEA). Worldwide Wind Capacity Reaches 744 Gigawatts—An Unprecedented 93 Gi- Ga watts Added in 2020. Available online: <https://wwindea.org/worldwide-wind-capacity-reaches-744-gigawatts/> (accessed on 17 June 2021).
- Lee, J.; Zhao, F. Global Wind Energy Council (GWEC). Available online: <https://gwec.net/wp-content/uploads/2021/03/GWEC-Global-Wind-Report-2021.pdf> (accessed on 10 September 2021).
- Global Energy Statistical Yearbook. Electricity Production. 2021. Available online: <https://yearbook.enerdata.net/electricity/world-electricity-production-statistics.html> (accessed on 10 September 2021).
- Kluskens, N.; Vasseur, V.; Benning, R. Energy Justice as Part of the Acceptance of Wind Energy: An Analysis of Limburg in The Netherlands. *Energies* 2019, 12, 4382
- Dimitris, A.L.; Katsaprakakis, D.A.; Christakis, D.G. The exploitation of electricity production projects from Renewable Energy Sources for the social and economic development of remote communities. The case of Greece: An example to avoid. *Renew. Sustain. Energy Rev.* 2016, 54, 341–349.
- Mishnaevsky, L., Jr.; Branner, K.; Petersen, H.N.; Beauson, J.; McGugan, M.; Sørensen, B.F. Materials for Wind Turbine Blades: An Overview. *Materials* 2017, 10, 1285.
- Sutherland, H.J. A Summary of the Fatigue Properties Wind Turbine Materials. Available online: <https://www.osti.gov/servlets/purl/12694> (accessed on 10 September 2021).
- Nagel, C.; Sondag, A.; Brede, M. Designing adhesively bonded joints for wind turbines. In *Adhesives in Marine Engineering*; Woodhead Publishing: Swanston, UK, 2012; pp. 46–71.
- Caithness Wind Farm Information Forum. Summary of Wind Turbine Accident Data to 31 March 2021. Available online: <http://www.caithnesswindfarms.co.uk/AccidentStatistics.htm> (accessed on 17 June 2021).
- Guo, J.; Jinfeng, C.L.; Jiang, C.D. Damage identification of wind turbine blades with deep convolutional neural networks. *Renew. Energy* 2021, 174, 122–133.

- Movsessian, A.; Cava, D.G.; Tcherniak, D.G. An artificial neural network methodology for damage detection: Demonstration on an operating wind turbine blade. *Mech. Syst. Signal Process.* 2021, 159, 107766
- Reddy, A.; Indra Gandhi, V.; Ravi, L.; Subramaniaswamy, V. Detection of Cracks and damage in wind turbine blades using artificial intelligence-based image analytics. *Measurement* 2019, 147, 106823.
- Dua, Y.; Zhoua, S.; Jing, X.; Peng, Y.; Wu, H.; Kwok, N. Damage detection techniques for wind turbine blades: A review. *Mech. Syst. Signal Process.* 2020,