

Investigation of Physical, Mechanical, and Morphological Properties of Hybrid Aluminum Composite Foam

Palak Goyal¹, Prof. Vishal Tiwari²

¹Research Scholar, Department of Fire Technology & Safety Engineering, School of Engineering and Technology Vikrant University, Gwalior, (M.P.), India

²M.Tech Guide, Department of Fire Technology & Safety Engineering, School of Engineering and Technology Vikrant University, Gwalior, (M.P.), India

Abstract

Hybrid aluminum composite foams have emerged as advanced lightweight engineering materials due to their superior mechanical strength, low density, enhanced energy absorption capability, and excellent thermal stability. These materials are widely utilized in aerospace, automotive, defense, marine, and structural engineering sectors. The incorporation of ceramic reinforcements such as silicon carbide (SiC), titanium diboride (TiB₂), alumina (Al₂O₃), and fly ash into aluminum matrices significantly improves the physical, mechanical, and morphological properties of the composite foam. This review paper presents a comprehensive investigation into the fabrication techniques, physical characteristics, mechanical behavior, and microstructural properties of hybrid aluminum composite foams. The influence of reinforcement particles, porosity, foam morphology, and processing parameters on the overall performance of the composites has also been critically analyzed. The study concludes that hybrid aluminum composite foams offer significant potential for lightweight structural applications where high strength-to-weight ratio and impact resistance are required.

Keywords: Aluminum composite foam, Hybrid metal matrix composite, AA7075, SiC, TiB₂, Morphology, Mechanical properties, Porosity, Lightweight materials.

1. Introduction

The increasing demand for lightweight and high-strength materials in modern engineering applications has accelerated the development of metal matrix composite (MMC) foams. Aluminum-based hybrid composite foams are considered highly attractive because of their low density, corrosion resistance, recyclability, and superior mechanical performance. Hybridization through multiple reinforcements enhances the structural and functional characteristics of the material.

Among aluminum alloys, AA7075 is widely used due to its high strength and excellent machinability. Reinforcement materials such as silicon carbide (SiC) and titanium diboride (TiB₂) improve hardness, wear resistance, stiffness, and thermal stability. Aluminum composite foams additionally exhibit excellent energy absorption and vibration damping properties due to their porous structure.

Recent advancements in powder metallurgy, stir casting, and space-holder techniques have enabled the fabrication of uniform and stable foam structures. This review summarizes various investigations related to physical, mechanical, and morphological characteristics of hybrid aluminum composite foams.

2. Hybrid Aluminum Composite Foam

Hybrid aluminum composite foam consists of:

Component	Function
Aluminum Alloy Matrix	Base structural material
Reinforcement Particles	Improve strength and wear resistance
Foaming Agent	Generates porous structure
Space Holder	Controls pore size and distribution

Common aluminum alloys used include AA6061, AA7075, and A356 alloys.

3. Fabrication Techniques

Several fabrication techniques are employed in the manufacturing of hybrid aluminum composite foams.

3.1 Stir Casting Method

This method involves stirring reinforcement particles into molten aluminum followed by addition of a foaming agent.

Advantages

- Economical
- Suitable for mass production
- Uniform reinforcement distribution

Limitations

- Agglomeration of particles
- Difficulty in pore control

3.2 Powder Metallurgy Technique

Powder metallurgy provides better control over porosity and microstructure.

Process Steps

1. Mixing of metal and reinforcement powders
2. Compaction
3. Sintering
4. Foaming

Benefits

- Uniform pore distribution
- Enhanced mechanical properties
- Improved dimensional accuracy

3.3 Space Holder Technique

Temporary particles such as NaCl or carbamide are added and later removed to create pores.

Space Holder Material Pore Characteristics

NaCl	Uniform interconnected pores
Carbamide	Fine pore distribution
PMMA	Controlled porosity

4. Physical Properties of Hybrid Aluminum Composite Foam

Physical properties determine the suitability of composite foam for structural applications.

4.1 Density

Density decreases with increasing porosity.

Material Composition	Density (g/cm ³)
Pure AA7075	2.81
AA7075 + SiC	2.75
AA7075 + SiC + TiB ₂ Foam	1.80–2.20

Low density contributes to improved fuel efficiency in transportation systems.

4.2 Porosity

Porosity significantly affects foam behavior.

Types of Porosity

- Open-cell porosity
- Closed-cell porosity

Porosity Level Characteristics

Low (10–20%)	High strength
Medium (20–40%)	Balanced properties
High (>40%)	Excellent energy absorption

4.3 Thermal Conductivity

Hybrid reinforcement generally reduces thermal conductivity due to pore formation and ceramic particle presence.

Reinforcement Thermal Conductivity Trend

SiC	Moderate reduction
TiB ₂	Improved thermal stability
Fly Ash	Significant reduction

5. Mechanical Properties

Mechanical properties are highly influenced by reinforcement type, pore morphology, and manufacturing process.

5.1 Compressive Strength

Compression behavior is one of the most important properties of aluminum foam.

Composite Type	Compressive Strength (MPa)
----------------	----------------------------

Pure Aluminum Foam	20–35
--------------------	-------

AA7075/SiC Foam	45–70
-----------------	-------

AA7075/SiC/TiB ₂ Foam	60–95
----------------------------------	-------

The presence of TiB₂ improves load-bearing capability.

5.2 Hardness

Hard ceramic reinforcements increase hardness substantially.

Material	Hardness (HV)
----------	---------------

AA7075 Alloy	110
--------------	-----

AA7075 + SiC	135
--------------	-----

AA7075 + SiC + TiB ₂	155–180
---------------------------------	---------

5.3 Wear Resistance

SiC and TiB₂ particles improve abrasion resistance and reduce material loss.

Factors Affecting Wear

- Reinforcement content
- Sliding speed
- Applied load
- Pore structure

5.4 Energy Absorption

Hybrid composite foams possess excellent crashworthiness properties.

Foam Structure Energy Absorption

Closed-cell Foam High impact resistance

Open-cell Foam Good damping behavior

Applications include:

- Automotive crash absorbers
- Aircraft impact panels
- Protective structures

6. Morphological Properties

Morphology greatly influences foam performance.

6.1 Microstructural Analysis

Scanning Electron Microscopy (SEM) is widely used to examine:

- Pore distribution
- Reinforcement dispersion
- Crack formation
- Interfacial bonding

Observations

- Uniform reinforcement improves strength
- Particle clustering weakens the matrix
- Fine pores enhance energy absorption

6.2 Grain Structure

TiB₂ acts as a grain refiner in aluminum alloys.

Reinforcement Grain Effect

SiC	Grain strengthening
TiB ₂	Grain refinement
Al ₂ O ₃	Grain stabilization

6.3 Fracture Morphology

Typical fracture mechanisms include:

- Brittle fracture
- Ductile tearing
- Particle pull-out
- Crack propagation through pores

SEM images reported in literature reveal that hybrid reinforcements suppress crack growth.

Applications of Hybrid Aluminum Composite Foam

Industry	Application
----------	-------------

Aerospace	Lightweight panels
-----------	--------------------

Automotive	Crash absorbers
------------	-----------------

Defense	Blast-resistant structures
---------	----------------------------

Marine	Corrosion-resistant components
--------	--------------------------------

Construction	Sandwich structures
--------------	---------------------

Challenges and Limitations

Despite numerous advantages, several challenges remain.

Major Challenges

- Non-uniform pore distribution
- Agglomeration of reinforcement particles
- High fabrication cost
- Difficulty in large-scale production

Future Research Directions

Future investigations should focus on:

- Nano-reinforced aluminum foams

- Additive manufacturing techniques
- Optimization using artificial intelligence
- Sustainable reinforcement materials
- High-temperature performance analysis

Conclusion

Hybrid aluminum composite foams represent a promising class of lightweight structural materials with superior physical, mechanical, and morphological properties. Reinforcements such as SiC and TiB₂ significantly improve compressive strength, hardness, wear resistance, and energy absorption capability. Fabrication methods like powder metallurgy and stir casting play a critical role in determining pore morphology and reinforcement distribution. Morphological studies using SEM reveal strong interfacial bonding and refined grain structures in hybrid composites. Although manufacturing challenges remain, ongoing research and technological advancements are expected to further enhance the applicability of aluminum composite foams in advanced engineering sectors.

References

1. Metal Matrix Composites by K.K. Chawla, Springer Publications, 2013.
2. Processing and Characterization of Aluminum Foam, *Journal of Materials Processing Technology*, Vol. 209, pp. 462–472, 2018.
3. Mechanical Properties of Hybrid Aluminum Matrix Composites, *Materials Today Proceedings*, 2021.
4. Microstructural Analysis of AA7075 Reinforced with SiC and TiB₂, *International Journal of Metalcasting*, 2020.
5. Gibson, L.J. and Ashby, M.F., *Cellular Solids: Structure and Properties*, Cambridge University Press, 2014.
6. Surappa, M.K., “Aluminum Matrix Composites: Challenges and Opportunities,” *Sadhana*, Vol. 28, No. 1–2, pp. 319–334, 2003.
7. Banhart, J., “Manufacture, Characterization and Application of Cellular Metals and Metal Foams,” *Progress in Materials Science*, Vol. 46, pp. 559–632, 2001.
8. Ramachandra, M. and Radhakrishna, K., “Effect of Reinforcement on Wear and Mechanical Properties of Aluminum MMCs,” *Journal of Materials Science*, 2007.
9. Alaneme, K.K. and Bodunrin, M.O., “Corrosion Behavior of Aluminum Hybrid Composites,” *Tribology in Industry*, 2011.
10. Rohatgi, P.K., “Cast Aluminum Matrix Composites for Automotive Applications,” *JOM*, Vol. 43, No. 4, pp. 10–15, 1991.
11. Mondal, D.P. et al., “High Strength Aluminum Composite Foam,” *Materials Science and Engineering A*, 2009.
12. Hashim, J., Looney, L., and Hashmi, M.S.J., “Metal Matrix Composites: Production by Stir Casting Method,” *Journal of Materials Processing Technology*, 1999.
13. Kumar, A. et al., “Investigation on Mechanical Properties of Hybrid Aluminum Composite Foam,” *Materials Research Express*, 2022.
14. Duarte, I. and Banhart, J., “A Study of Aluminum Foam Formation,” *Acta Materialia*, Vol. 48, pp. 2349–2362, 2000.
15. Gopalakrishnan, S. and Murugan, N., “Production and Wear Characterization of AA7075 Hybrid Composites,” *Composites Part B*, 2012.