

Sustainable High-Performance Cementitious Composites for Durable and Low-Carbon Civil Infrastructure

¹Vijay Saini, ²Hemant Kumar Agrawal

^{1,2} Assistant Professor

Jagannath University, Jaipur, India

Abstract

Concrete remains the dominant construction material, yet its cement-intensive production and exposure-driven deterioration impose substantial environmental and economic burdens. This paper develops a materials-focused framework for sustainable high-performance cementitious composites (SHPPCs) that combines supplementary cementitious materials (SCMs), recycled aggregate, fibre reinforcement, and durability-oriented mix design. A structured analytical program is presented using representative mixes and performance indicators for compressive strength, transport resistance, crack control, life-cycle carbon, and cost. The findings indicate that a hybrid binder containing ground-granulated blast-furnace slag and metakaolin can reduce modeled embodied carbon by 30–45% while maintaining or improving later-age strength and chloride resistance. The work translates material-selection principles into a practical design and testing sequence for civil infrastructure. It also identifies limitations associated with SCM variability, curing sensitivity, workability retention, and the need for local characterization. The paper is intended as a rigorous research-style reference for Civil Engineering Materials courses and early-stage material design studies.

Index Terms—Sustainable concrete, supplementary cementitious materials, recycled aggregate, durability, life-cycle assessment, fibre-reinforced cementitious composite.

I. INTRODUCTION

Civil infrastructure requires materials that satisfy strength, serviceability, durability, constructability, cost, and environmental objectives simultaneously. Ordinary Portland cement (OPC) concrete provides exceptional versatility, but binder manufacture is carbon intensive and many reinforced-concrete assets experience premature distress from chloride ingress, carbonation, sulfate attack, shrinkage cracking, and poor curing. A material solution therefore cannot be judged by 28-day strength alone; it must be evaluated as a coupled system of binder chemistry, pore structure, aggregate quality, interfacial transition zone, reinforcement, exposure, and maintenance strategy.

This paper investigates a practical SHPPC concept: a low water-to-binder matrix using OPC, slag, metakaolin, recycled coarse aggregate, and discrete fibres. Rather than presenting unverified laboratory measurements as field facts, the study uses transparent, representative analytical datasets to demonstrate how a research program can compare alternatives. This distinction is important for academic integrity and for responsible adoption in design practice.

A. Research Objectives

- Establish performance-selection criteria for civil engineering materials in aggressive exposure conditions.
- Quantify representative effects of hybrid SCM binders on strength, transport, and embodied-carbon indicators.
- Provide equations, experimental workflow, tables, diagrams, and graphs suitable for an IEEE-formatted academic paper.
- Recommend a validation protocol for local materials and project specifications.

II. LITERATURE BACKGROUND

SCMs alter hydration kinetics and microstructure. Slag contributes latent hydraulic reactivity and commonly supports later-age strength; metakaolin provides high pozzolanic reactivity and refines pore structure. Their combined use can reduce clinker demand while balancing early-age and later-age performance. Recycled aggregate can conserve natural resources but requires moisture correction and grading control because adhered mortar increases absorption and variability. Fibres bridge cracks and improve post-cracking response, particularly where restrained shrinkage or fatigue is relevant.

Material family	Primary function	Key risk	Quality-control indicator
OPC	Early strength and alkalinity	High CO ₂ intensity	Blaine fineness; strength class
GGBS	Later-age strength; lower clinker	Slow reaction in cold curing	Glass content; fineness
Metakaolin	Pore refinement; early reactivity	Higher water demand	LOI; particle size
Recycled aggregate	Resource conservation	Absorption and impurities	Water absorption; density
Steel/PP fibre	Crack bridging	Balling; workability loss	Dosage; aspect ratio

Table I. Functional roles and control indicators for selected constituent materials.

A. Durability as a Materials Property

Durability is governed by transport and reaction. A dense, well-cured paste reduces the connectivity of capillary pores; a sound interfacial transition zone limits preferential pathways around aggregate. Material design must therefore connect mixture proportions to measurable proxies such as electrical resistivity, sorptivity, rapid chloride migration coefficient, mass loss, and restrained-shrinkage crack width.

III. MATERIALS AND RESEARCH METHODOLOGY

The proposed program compares five binder systems at constant total binder content of 420 kg/m³ and target slump flow appropriate for structural placement. Mixes are proportioned by absolute volume. Recycled coarse aggregate replacement is limited to 25% in the reference matrix; this level is selected to demonstrate a conservative, quality-controlled pathway rather than a universal optimum. Superplasticizer dosage is adjusted to maintain workability without increasing water content.

Mix ID	OPC (%)	GGBS (%)	MK (%)	RCA (%)	Fibre (vol.%)	w/b
M0	100	0	0	0	0	0.38
M1	70	30	0	0	0.38	
M2	65	25	10	25	0	0.36
M3	63	25	10	25	0.50	0.36
M4	60	25	10	25	0.75	0.34

Table II. Representative mixture matrix. MK = metakaolin; RCA = recycled coarse aggregate.

A. Governing Mix-Design Equations

The water-to-binder ratio is defined as $w/b = M_w / (M_c + M_s + M_m)$, where M_w is mixing water and M_c , M_s , and M_m are masses of cement, slag, and metakaolin. The absolute-volume

constraint is $\Sigma(M_i/\rho_i) + V_{\text{air}} = 1.00 \text{ m}^3$. These equations ensure that changes in binder composition remain volumetrically consistent.

Compressive strength can be represented by a calibrated inverse water-binder relation: $f_c' = A(B/(w/b))^n$, where A, B, and n are experimentally fitted for the material family. A carbon indicator is calculated as $EC = \Sigma(M_i \cdot EF_i)$, where EF_i is the cradle-to-gate emission factor of constituent i. These are design equations, not replacements for project-specific standards.

IV. EXPERIMENTAL PROGRAM AND TESTING PLAN

Specimens should be batched in a controlled laboratory using a moisture-corrected aggregate condition. Fresh tests include slump flow, air content, temperature, and density. Hardened tests include compressive strength at 7, 28, 56, and 90 days; splitting tensile strength; elastic modulus; water absorption; sorptivity; electrical resistivity; chloride migration; drying shrinkage; and fibre pull-out or flexural residual strength where applicable.

Property	Suggested framework test	Age / condition	Decision use
Workability	Slump/slump flow	Fresh	Placement feasibility
Compressive strength	Cube/cylinder compression	7–90 d	Structural class
Transport	Chloride migration / resistivity	28–90 d	Rebar corrosion risk
Shrinkage	Length change	Up to 90 d	Crack-control risk
Toughness	Flexural residual response	28 d	Post-crack capacity
Carbon	Inventory-based calculation	Per m ³	Environmental comparison

Table III. Recommended performance-test matrix.

Figure 1 shows the proposed materials-to-performance pathway. Input characterization must precede batching because recycled aggregate moisture, SCM fineness, and admixture compatibility can materially alter the actual mixture response.




Fig. 1. Representative relationship between SCM replacement and 28-day compressive strength.

V. RESULTS AND DISCUSSION

A. Strength Development

The modeled results show a modest early-age penalty for slag-rich matrices, followed by improved later-age strength in the hybrid binder. Metakaolin offsets part of the early-age delay through nucleation and pozzolanic reaction, while lower w/b supports matrix densification. Fibre dosage has little direct effect on cube strength but can influence entrapped air and therefore must be controlled through mixing sequence and admixture adjustment.




Fig. 2. Representative compressive-strength development for a control and hybrid-binder matrix.

Age	M0 control (MPa)	M2 hybrid (MPa)	M3 fibre hybrid (MPa)
7 d	26	24	23
28 d	41	43	42
56 d	47	52	51
90 d	50	57	56

Table IV. Illustrative compressive-strength dataset for comparative analysis.

At 90 days the hybrid matrix reaches 57 MPa versus 50 MPa for the control. The trend should be interpreted as a plausible material response, not as a substitute for replicated testing. Statistical treatment should report mean, standard deviation, coefficient of variation, and confidence intervals for every test age.

B. Transport Resistance and Service Life

A lower chloride migration coefficient indicates a less connected pore network and can delay corrosion initiation in chloride-exposed reinforced concrete. The hybrid binder achieves the greatest benefit after continued curing because secondary reaction products refine capillary pathways. This advantage is sensitive to curing temperature, moisture availability, and the chloride-binding behavior of the specific binder system.




Fig. 3. Representative reduction in chloride migration coefficient with a hybrid binder.

For conceptual service-life screening, chloride ingress may be modeled using the error-function solution of Fick's second law: $C(x,t) = C_s[1 - \text{erf}(x/(2\sqrt{D_{\text{app}}t}))]$, where C_s is surface chloride content, x is cover depth, and D_{app} is apparent diffusion coefficient. Corrosion initiation is considered when C at reinforcement depth reaches a chosen threshold. Project design must use exposure-specific parameters and applicable standards.

C. Crack Control and Fibre Contribution

Fibres enhance residual load capacity after first cracking by transferring stress across an opening crack. Their contribution is influenced by fibre type, aspect ratio, orientation, bond, matrix strength, and casting flow. In practical slabs and overlays, fibre reinforcement may reduce crack width and improve impact/fatigue behavior; however, it does not remove the need for joints, cover, shrinkage control, and reinforcement design.




Fig. 4. Conceptual normalized post-crack response of plain and fibre-reinforced matrices.

Fibre volume (%)	Fresh-workability trend	Residual-load expectation	Typical constructability action
0.00	Baseline	Low	Conventional mixing
0.50	Moderate reduction	Moderate	Add fibres gradually
0.75	Noticeable reduction	Higher	Verify pumpability
1.00+	High reduction	High	Trial batch required

Table V. Fibre-dose implications for a cementitious composite.

D. Life-Cycle Carbon and Cost Interpretation

Material sustainability should be evaluated per functional unit—for example, one cubic metre of concrete meeting a stated strength and exposure class. A lower-carbon mixture that requires premature repair may not yield the best life-cycle outcome. Conversely, a slightly higher-cost fibre or SCM addition can be rational when it reduces maintenance, traffic disruption, or corrosion risk.




Fig. 5. Illustrative embodied-carbon comparison across five representative mix scenarios.

Scenario	Binder strategy	Embodied CO ₂ (kg/m ³)	Relative material cost	Durability outlook
A	100% OPC	410	1.00	Baseline
B	30% slag	365	0.98	Improved
C	25% slag + 10% MK	320	1.05	High
D	Hybrid + RCA	270	1.02	High, dependent
E	Optimized hybrid + fibre	240	1.12	Very high

Table VI. Representative cradle-to-gate material indicators; local EPDs and transport distances must be used for project decisions.

VI. MICROSTRUCTURAL INTERPRETATION

The performance trends can be explained by a coupled microstructural mechanism. Slag hydration and metakaolin pozzolanic reaction consume calcium hydroxide and generate additional calcium-silicate-hydrate or aluminosilicate phases. This reduces the size and continuity of pores when curing is adequate. Recycled aggregate introduces old mortar and a potentially weaker interfacial zone, but preconditioning, grading, and the refined new paste can mitigate the penalty. Fibres principally act at the crack scale rather than by increasing matrix compressive strength.

Scale	Dominant feature	Material lever	Engineering outcome
Nano/micro	Hydration products and pores	SCM type; curing	Lower permeability
Meso	ITZ and aggregate	RCA quality; packing	More stable stiffness
Macro	Cracks and joints	Fibres; shrinkage control	Higher toughness
Asset	Exposure and maintenance	Cover; mix class	Longer service life

Table VII. Multiscale interpretation of sustainable composite performance.

VII. DESIGN OF EXPERIMENTS AND DATA ANALYSIS

A factorial design can efficiently evaluate the interaction of slag content, metakaolin content, recycled-aggregate replacement, fibre volume, and w/b. At minimum, three replicate specimens per response-age combination are recommended. Randomize specimen order, record raw material batches, and predefine acceptance criteria. Analysis of variance can identify significant main effects and interactions; regression or response-surface methods can then estimate a feasible region rather than a single “optimum.”

A normalized multi-criteria performance index may be written as $PI = w_s S^* + w_d D^* + w_c C^* + w_k K^*$, where S^* , D^* , C^* , and K^* are normalized strength, durability, carbon, and cost scores and the weights sum to one. The weights should be agreed with the asset

owner; a marine structure appropriately places more emphasis on durability than a lightly exposed pavement.

Response	Preferred direction	Example normalization	Suggested minimum replication
Strength	Maximize	$S^* = f_c / f_{c,target}$	3
Chloride resistance	Maximize	$D^* = D_{ref} / D_{app}$	3
Carbon	Minimize	$C^* = EC_{ref} / EC$	1 inventory sensitivity +
Cost	Minimize	$K^* = Cost_{ref} / Cost$	1 estimate sensitivity +

Table VIII. Multi-criteria decision-analysis structure.

VIII. PRACTICAL SPECIFICATION GUIDANCE

Specifications should state outcomes and verification methods rather than merely mandating a material name. A performance-based clause may define minimum 56-day compressive strength, maximum chloride migration coefficient, maximum drying shrinkage, fresh-workability range, and documentation requirements for recycled aggregate and SCM source control. Prequalification trial batches are especially important where local by-product materials vary seasonally.

- Require certified source information and batch traceability for binder constituents.
- Set moisture correction and absorption limits for recycled aggregates.
- Define curing regime explicitly; SCM-rich systems are curing sensitive.
- Use mock-up placements to verify finishing, pumping, and fibre dispersion.
- Review environmental declarations using the same functional unit and system boundary.

IX. LIMITATIONS, ETHICS, AND REPRODUCIBILITY

This paper contains a representative analytical dataset prepared to demonstrate research-paper structure and material interpretation. It is not a report of completed laboratory testing. Any academic submission should clearly distinguish literature evidence, proposed methods, and experimentally obtained results. For real project use, all mixture proportions, emissions factors, and strength/durability values must be verified from local trial batches, accredited test laboratories, and applicable code provisions.

Reproducibility requires reporting cement and SCM chemistry, aggregate grading and absorption, admixture type, mixing sequence, specimen geometry, curing regime, test standard, number of replicates, raw data, and statistical treatment. These details frequently explain differences between apparently similar mixtures.

X. CONCLUSIONS

1. Sustainable high-performance cementitious composites should be assessed through strength, transport resistance, crack control, constructability, carbon, and cost—not compressive strength alone.
2. A hybrid slag–metakaolin binder can plausibly lower clinker demand and improve later-age transport resistance when proportioning and curing are controlled.
3. Recycled aggregate is viable within a quality-managed system, but its absorption, grading, and contamination require explicit control.
4. Fibres enhance post-crack behavior and should be selected with workability and placement method in view.
5. Performance-based specifications and locally validated trial batches are essential before field adoption.

ACKNOWLEDGMENT

The author acknowledges the academic setting of Jagannath University, Jaipur, and the wider civil-engineering community whose standards, technical literature, and laboratory practice guide responsible material innovation.

REFERENCES

- [1] ASTM C39/C39M, Standard Test Method for Compressive Strength of Cylindrical Concrete Specimens.
- [2] ASTM C1202, Standard Test Method for Electrical Indication of Concrete's Ability to Resist Chloride Ion Penetration.
- [3] ASTM C1585, Standard Test Method for Measurement of Rate of Absorption of Water by Hydraulic-Cement Concretes.
- [4] ACI Committee 318, Building Code Requirements for Structural Concrete, American Concrete Institute.
- [5] ACI Committee 232, Use of Fly Ash in Concrete, American Concrete Institute.
- [6] ACI Committee 233, Slag Cement in Concrete and Mortar, American Concrete Institute.
- [7] EN 206, Concrete—Specification, Performance, Production and Conformity.
- [8] P. K. Mehta and P. J. M. Monteiro, Concrete: Microstructure, Properties, and Materials, 4th ed. McGraw-Hill.
- [9] K. L. Scrivener, V. M. John, and E. M. Gartner, "Eco-efficient cements," Cement and Concrete Research, vol. 114, pp. 2–26, 2018.
- [10] J. Thomas, A. Sethy, and U. C. Sahoo, "Sustainable concrete materials and durability," Construction and Building Materials, review literature.
- [11] fib Model Code for Concrete Structures, International Federation for Structural Concrete.
- [12] ISO 14040, Environmental Management—Life Cycle Assessment—Principles and Framework.

APPENDIX A. MIX-DESIGN CALCULATION EXAMPLE

For M2, total binder $B = 420 \text{ kg/m}^3$ and $w/b = 0.36$. Therefore mixing water $M_w = 0.36 \times 420 = 151.2 \text{ kg/m}^3$. Binder masses are $OPC = 273 \text{ kg/m}^3$, $GGBS = 105 \text{ kg/m}^3$, and $metakaolin = 42 \text{ kg/m}^3$. Aggregate masses are then determined through the absolute-volume equation after allowing for entrapped air and admixture volume. The example demonstrates the calculation sequence; final aggregate proportions must use measured specific gravities and grading.

Constituent	Mass (kg/m ³)	Specific gravity	Absolute volume (m ³)
Water	151.2	1.00	0.151
OPC	273.0	3.15	0.087
GGBS	105.0	2.90	0.036
Metakaolin	42.0	2.60	0.016
Aggregates + air	Balance	—	0.710

Table A-I. Illustrative absolute-volume calculation.

APPENDIX B. QUALITY-ASSURANCE CHECKLIST

- Verify batch certificates and record SCM source, lot, and fineness.
- Measure aggregate moisture immediately before mixing and adjust batch water.
- Use a fixed mixing sequence and document fibre addition rate.
- Cure specimens under controlled temperature and moisture.
- Report individual measurements, mean, standard deviation, and exclusions.
- Retain raw data, specimen photographs, and calculation sheets.

This appendix is designed to make a student laboratory report auditable and repeatable. It can be adapted into a project-method statement or a laboratory data sheet.

APPENDIX C. REPRESENTATIVE RAW-DATA REGISTER

A raw-data register prevents later ambiguity in the interpretation of material behavior. Each line should identify specimen code, batch number, test date, curing condition, operator, instrument, and

measured value. The following layout may be used for laboratory reporting.

Specimen	Mix	Age (d)	Failure load (kN)	Strength (MPa)	Remarks
C-01	M2	28	812	43.1	Normal failure
C-02	M2	28	798	42.3	Normal failure
C-03	M2	28	825	43.8	Normal failure
F-01	M3	28	804	42.7	Fibre dispersed
F-02	M3	28	790	41.9	Slight air increase

Table C-I. Example raw-data register format.

Before reporting a mean value, confirm that specimen geometry, loading rate, and failure mode meet the selected test standard. Any excluded value should be retained in the record with a written technical reason.

APPENDIX D. EXPOSURE-BASED MATERIAL SELECTION

The material solution must respond to the exposure class. The selection matrix below is a preliminary decision aid and is not a substitute for the exposure-class requirements of the governing code.

Exposure	Dominant mechanism	Preferred material response	Verification
Interior dry	Shrinkage finishability	Moderate SCM; controlled w/b	Strength + shrinkage
Marine splash	Chloride ingress	Low transport binder; adequate cover	Migration + resistivity
Sulfate soil	Chemical attack	Sulfate-resistant binder system	Expansion test
Freeze-thaw	Hydraulic pressure	Air entrainment; sound aggregate	Freeze-thaw cycles
Pavement	Abrasion / fatigue	Hard aggregate; fibres as needed	Abrasion + flexure

Table D-I. Exposure-driven selection framework.

A sound specification pairs the selected material response with a measurable acceptance test. This approach avoids vague claims such as "durable concrete" without a verification pathway.

APPENDIX E. STATISTICAL REPORTING TEMPLATE

For n replicate measurements x_i , the sample mean is $\bar{x} = (1/n)\sum x_i$ and the sample standard deviation is $s = \sqrt{[\sum (x_i - \bar{x})^2 / (n - 1)]}$. The coefficient of variation is $CV = 100s/\bar{x}$ (%). These measures should accompany all reported material-performance values.

Response	n	Mean	Std. dev.	CV (%)	Acceptance statement
28-day strength, M2	3	43.1 MPa	0.75 MPa	1.74	Meets target
Migration coefficient, M2	3	5.0	0.30	6.00	Below limit
Slump flow, M3	3	610 mm	18 mm	2.95	Within range

Table E-I. Example summary statistics for a laboratory report.

Graphs should show units, axes, sample age, and uncertainty bars where data are experimental. The charts in the main text are clearly labeled as representative analytical illustrations.

APPENDIX F. IMPLEMENTATION ROADMAP

The following staged route can be used to translate laboratory material development into a field trial. At each stage, proceed only after acceptance criteria are satisfied.

6. Characterize local cement, SCM, recycled aggregate, water, and admixture compatibility.
7. Complete trial batches and establish fresh-property control limits.
8. Test strength, transport, shrinkage, and constructability at the intended exposure level.
9. Prepare a pilot placement with documented mixing, delivery, finishing, and curing.

10. Review results with structural designer, contractor, and owner before specification adoption.

This roadmap reinforces the central conclusion of the paper: high-quality material innovation depends on transparent testing and controlled implementation, not only on nominal mixture composition.

APPENDIX G. SYMBOLS AND ABBREVIATIONS

Symbol / term	Meaning	Unit or note
w/b	Water-to-binder ratio	Mass ratio
f_c'	Compressive strength	MPa
D_{app}	Apparent diffusion coefficient	m ² /s
EC	Embodied-carbon indicator	kg CO ₂ e/m ³
GGBS	Ground-granulated blast-furnace slag	SCM
MK	Metakaolin	SCM
RCA	Recycled coarse aggregate	Aggregate replacement
ITZ	Interfacial transition zone	Paste-aggregate interface

Table G-I. Symbols and abbreviations used in this paper.

The notation is provided to support consistent interpretation of the equations and material terms used throughout the manuscript. Parameters remain subject to calibration for the locally selected materials and environmental conditions.

APPENDIX H. CHEMICAL AND PHYSICAL CHARACTERIZATION

The technical scope of this topic is governed by binder chemistry, particle-size distribution, and mineralogical composition. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines X-ray fluorescence, X-ray diffraction, laser diffraction, thermogravimetry, and loss-on-ignition testing. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern reactivity, water demand, setting, and long-term pore refinement. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations,

and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX I. FRESH-STATE RHEOLOGY

The technical scope of this topic is governed by yield stress, plastic viscosity, thixotropy, and particle packing. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines slump flow, V-funnel time, rheometry, air content, density, and visual stability index. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern pumping pressure, segregation resistance, finishing window, and fibre dispersion. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations,

and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX J. HYDRATION AND CURING

The technical scope of this topic is governed by early hydration, secondary pozzolanic reaction, internal humidity, and temperature history. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines semi-adiabatic calorimetry, maturity monitoring, internal relative-humidity sensors, and mass tracking. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern early strength, thermal cracking risk, autogenous shrinkage, and later-age durability. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations,

and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX K. RECYCLED-AGGREGATE CONDITIONING

The technical scope of this topic is governed by adhered mortar, absorption, angularity, contamination, and pre-saturation state. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines grading, oven-dry density, water absorption, crushing value, and image-based impurity assessment. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern effective water content, interfacial-zone quality, stiffness, and variability. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from

independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX L. DRYING AND AUTOGENOUS SHRINKAGE

The technical scope of this topic is governed by moisture loss, self-dissiccation, restraint, creep relaxation, and member geometry. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines length-change prisms, sealed autogenous specimens, ring tests, and environmental logging. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern crack initiation time, crack width, joint spacing, and curing demand. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be

randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX M. CHLORIDE-INDUCED CORROSION

The technical scope of this topic is governed by chloride transport, binding, cover quality, electrical resistivity, and steel threshold. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines bulk diffusion, migration testing, surface resistivity, chloride profiling, and half-cell monitoring. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern corrosion-initiation period, propagation risk, cover specification, and maintenance interval. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be

randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX N. CARBONATION PERFORMANCE

The technical scope of this topic is governed by carbon-dioxide diffusion, pore saturation, alkalinity loss, and curing quality. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines accelerated carbonation depth, natural-exposure monitoring, phenolphthalein indication, and resistivity. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern depassivation depth, cover adequacy, indoor exposure response, and service-life uncertainty. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from

independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX O. SULFATE AND ACID EXPOSURE

The technical scope of this topic is governed by ion ingress, expansive reaction products, decalcification, and permeability. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines mass change, expansion, strength retention, solution chemistry, and microscopy. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern binder compatibility, lining need, inspection frequency, and exposure-class limits. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations,

and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX P. FREEZE-THAW AND SCALING

The technical scope of this topic is governed by critical saturation, entrained-air stability, hydraulic pressure, and salt scaling. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines air-void analysis, dynamic modulus, mass loss, visual rating, and surface scaling cycles. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern air-content target, aggregate soundness, finishing control, and winter durability. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations,

and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX Q. FIRE AND ELEVATED TEMPERATURE

The technical scope of this topic is governed by thermal incompatibility, moisture pressure, microcracking, and fibre melting. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines furnace exposure, residual strength, mass loss, ultrasonic pulse velocity, and thermal analysis. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern spalling risk, residual capacity, repair classification, and fire-resistant detailing. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be

randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX R. NON-DESTRUCTIVE EVALUATION

The technical scope of this topic is governed by wave propagation, surface hardness, electrical response, and defect localization. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines rebound hammer, ultrasonic pulse velocity, impact echo, resistivity mapping, and infrared thermography. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern uniformity screening, anomaly detection, test-location selection, and condition assessment. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from

independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX S. STRUCTURAL-SCALE VALIDATION

The technical scope of this topic is governed by size effect, reinforcement interaction, restraint, casting direction, and construction variability. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines beams, slabs, pull-out specimens, restrained panels, and instrumented pilot placements. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern crack distribution, deflection, anchorage, field constructability, and design-model calibration. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from

independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX T. LIFE-CYCLE ASSESSMENT BOUNDARIES

The technical scope of this topic is governed by functional unit, allocation, transport, energy mix, service life, and end-of-life scenario. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines environmental product declarations, verified inventories, scenario analysis, and sensitivity analysis. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern transparent carbon comparison, burden shifting, procurement choices, and reporting credibility. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production.

Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX U. LIFE-CYCLE COST AND ASSET VALUE

The technical scope of this topic is governed by initial material cost, construction time, inspection, repair, closure, and residual value. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines discounted cash flow, probabilistic deterioration, maintenance scenarios, and user-cost estimation. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern whole-life value, intervention timing, risk allocation, and owner decision making. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX V. UNCERTAINTY AND RELIABILITY

The technical scope of this topic is governed by batch variability, test error, model form, environmental loading, and parameter correlation. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines replication, control charts, bootstrap intervals, Monte Carlo simulation, and reliability indices. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern characteristic values, safety margins, robust optimization, and confidence in acceptance. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX W. SCALE-UP AND FUTURE RESEARCH

The technical scope of this topic is governed by supply consistency, mixing energy, workforce practice, sensor data, and circular-material availability. These variables are coupled rather than independent: a change introduced to improve one response may alter fresh behavior, curing demand, or another durability mechanism. For that reason, the proposed composite should be evaluated as a complete material system under a declared exposure and construction process. Literature values are useful for screening, but the design value must be derived from the actual constituent sources and production conditions.

A defensible characterization program combines multi-site round-robin testing, field demonstrators, digital batch records, and long-term exposure stations. No single indicator is sufficient. Screening tests provide rapid comparison, whereas mechanism-specific tests explain why a mixture changes and whether that change is likely to persist. Equipment calibration, specimen conditioning, temperature, operator procedure, and reporting precision should be fixed before the first batch. Reference material and control specimens should be carried through the same sequence so that day-to-day laboratory drift can be detected.

The primary engineering decisions concern regional specifications, scalable quality assurance, data sharing, and responsible adoption. Acceptance limits should therefore connect a measured response to a design consequence. A statistically significant difference is not automatically an important engineering difference; effect size, uncertainty, constructability, and the cost of failure must also be considered. Conversely, a small improvement in a transport property can be valuable when deterioration is strongly governed by an initiation period and repair access is difficult.

For mixture comparison, the control and candidate materials should be tested at equal functional performance wherever possible. Comparing mixtures only at equal binder content can unfairly favor or penalize one system because strength class, workability, and curing sensitivity differ. A balanced comparison fixes the intended structural and exposure requirements, then optimizes proportions within those constraints. All deviations from the planned method

should be recorded contemporaneously rather than reconstructed after results are known.

Quality assurance begins with a sampling plan. At least three independent batches are preferable to multiple specimens cut from a single batch because batch-to-batch variance matters in production. Within each batch, specimen positions and test order should be randomized. The report should distinguish technical replicates from independent batch replicates, state the number of valid observations, and show dispersion. Outliers may be excluded only through a declared rule and a documented physical or procedural cause.

The interpretation should use both mechanism and evidence. Trends that agree with established material science remain hypotheses until supported by the measured chemistry, microstructure, or transport response of the studied system. Correlation between strength and durability is convenient but not universal; two matrices with similar compressive strength can have different pore connectivity, binding capacity, shrinkage, or cracking response. Multiple performance indicators are therefore retained in the proposed decision framework.

Field translation requires a hold point between laboratory optimization and routine supply. A pilot placement should reproduce the expected mixer type, batch volume, transport time, ambient condition, placing method, finishing practice, and curing system. Fresh properties should be measured at discharge and after the intended delay. Cores or companion specimens can then be compared with laboratory-cured specimens to quantify the field-to-laboratory relationship and update acceptance limits.

Finally, the result should be communicated with traceable units, test ages, uncertainty, and boundary conditions. Raw data and calculation sheets should accompany summary graphs. Where a performance claim depends on a model, the calibration data and sensitivity to uncertain parameters should be disclosed. This reporting discipline makes the study useful beyond a single mixture and supports responsible peer review, replication, and specification development.

APPENDIX X. ALKALI-SILICA REACTION

This research area is controlled by reactive silica, alkali availability, internal humidity, aggregate petrography, and supplementary binder chemistry. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes petrographic examination, accelerated mortar bars, concrete prisms, pore-solution analysis, and long-duration exposure. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about expansion control, aggregate approval, SCM dosage, and moisture management. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge

consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX Y. ABRASION AND EROSION

This research area is controlled by surface hardness, aggregate mineralogy, paste quality, finishing, impact, and hydraulic action. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes rotating-cutter abrasion, underwater abrasion, mass loss, profile scanning, and visual mapping. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about floor serviceability, spillway performance, pavement wear, and repair interval. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX Z. FATIGUE AND CYCLIC LOADING

This research area is controlled by stress range, mean stress, crack initiation, fibre bridging, frequency, and environmental interaction. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes cyclic flexure, repeated compression, crack-mouth displacement, stiffness tracking, and acoustic emission. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about fatigue life, residual stiffness, crack control, and inspection planning. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AA. BOND WITH REINFORCEMENT

This research area is controlled by rib geometry, confinement, cover, matrix splitting strength, casting position, and corrosion. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes pull-out tests, beam-end tests, splice specimens, digital image correlation, and failure-surface examination. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about development length, anchorage reliability, crack spacing, and repair assessment. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AB. PERMEABILITY AND SORPTIVITY

This research area is controlled by capillary suction, saturation, pore connectivity, microcracking, and curing history. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes initial surface absorption, sorptivity, gas permeability, water penetration, and vacuum saturation. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about liquid ingress, protective-treatment need, quality grading, and service-life modeling. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from

the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AC. SELF-HEALING POTENTIAL

This research area is controlled by continued hydration, carbonate precipitation, crack width, moisture cycles, and engineered healing agents. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes repeated permeability, microscopy, crack-image analysis, resonant frequency, and recovery of stiffness. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about autogenous recovery, leakage control, durability restoration, and inspection intervals. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AD. GEOPOLYMER AND ALKALI-ACTIVATED OPTIONS

This research area is controlled by precursor chemistry, activator modulus, curing temperature, efflorescence, and shrinkage. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes calorimetry, spectroscopy, pore-solution analysis, strength testing, and leachate characterization. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about clinker reduction, early performance, chemical resistance, and safe field handling. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AE. BIO-BASED AND NATURAL FIBRES

This research area is controlled by fibre absorption, alkaline stability, interface bond, geometry, and biological variability. Each factor can change the apparent ranking of candidate mixtures, so a meaningful

comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes tensile testing, pull-out, microscopy, accelerated aging, moisture cycling, and flexural toughness. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about renewable reinforcement, crack bridging, durability risk, and local-material value. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AF. THREE-DIMENSIONAL CONCRETE PRINTING

This research area is controlled by extrudability, buildability, open time, interlayer bond, geometry, and process control. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes rheometry, filament geometry, layer loading, interlayer tension, imaging, and robotic process logs. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about automated construction, material efficiency, anisotropy control, and design freedom. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AG. PRECAST PRODUCTION

This research area is controlled by rapid strength, heat curing, dimensional tolerance, surface finish, lifting, and repetition. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes maturity, steam-curing records, release strength, dimensional inspection, and production control charts. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and

certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about cycle time, consistency, transport damage, connection quality, and factory decarbonization. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AH. PAVEMENT MATERIAL APPLICATION

This research area is controlled by flexural fatigue, joint behavior, abrasion, thermal gradient, drainage, and subgrade support. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes beam flexure, repeated loading, skid resistance, texture depth, and trial sections. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about slab thickness, joint performance, ride quality, maintenance, and traffic disruption. The interpretation should distinguish material capacity from structural demand and laboratory

acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AI. MARINE AND COASTAL APPLICATION

This research area is controlled by chlorides, wetting and drying, sulfate, abrasion, temperature, oxygen access, and cover cracking. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes tidal exposure blocks, chloride profiles, corrosion sensors, visual mapping, and surface resistivity. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about corrosion delay, splash-zone durability, inspection access, and whole-life resilience. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AJ. REPAIR-MATERIAL COMPATIBILITY

This research area is controlled by substrate moisture, stiffness mismatch, shrinkage, bond, permeability, and thermal movement. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes slant shear, pull-off bond, restrained shrinkage, permeability, and composite-beam response. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about debonding resistance, crack reflection, patch durability, and repair sequencing. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of

every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AK. DIGITAL MATERIAL PASSPORTS

This research area is controlled by source identity, batch composition, test results, environmental data, placement location, and revision history. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes structured data fields, QR-linked records, sensor integration, audit trails, and interoperable asset databases. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about traceability, maintenance knowledge, circular recovery, and accountable procurement. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge

consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AL. STANDARDIZATION AND CODE ADOPTION

This research area is controlled by test repeatability, safety factors, exposure definitions, conformity assessment, and stakeholder confidence. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes round-robin programs, precision statements, field demonstrations, committee review, and public consultation. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about harmonized acceptance, innovation pathways, designer confidence, and market scale. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship, drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.

APPENDIX AM. RESEARCH PRIORITIES

This research area is controlled by regional SCM availability, emerging waste streams, climate exposure, automation, monitoring, and social value. Each factor can change the apparent ranking of candidate mixtures, so a meaningful comparison begins with a declared material state, exposure condition, and functional requirement. The hybrid cementitious composite proposed in this paper should be treated as a platform that is adjusted through measured performance rather than as a fixed recipe transferable to every project.

The recommended evidence package includes long-term field sites, open datasets, coupled deterioration models, techno-economic analysis, and interdisciplinary trials. Test selection should cover both the governing mechanism and a property that can be used for routine quality control. A detailed method statement must define conditioning, specimen geometry, loading or exposure history, measurement interval, calculation, and reporting rule. Control specimens and certified reference materials improve confidence when the response is sensitive to equipment or operator judgment.

Results inform decisions about low-carbon infrastructure, resilient assets, circular construction, and evidence-based policy. The interpretation should distinguish material capacity from structural demand and laboratory acceleration from natural exposure. An acceleration regime is valuable only when it preserves the dominant field mechanism. If the accelerated test creates a different reaction, moisture state, or failure mode, its numerical ranking should not be extrapolated directly to service life.

Material variability should be treated quantitatively. Constituent lots, independent batches, and replicate specimens form different levels of variation and should not be pooled without explanation. A mixed-effects model or nested analysis can separate these sources when the program is sufficiently large. For a smaller study, transparent plots of every observation, batch means, and confidence intervals are more informative than an isolated average.

The mixture-design response must also be checked against production practicality. Powder content, aggregate shape, fibre volume, and admixture chemistry influence mixer demand, discharge consistency, pump pressure, finishing, and curing. A laboratory optimum that depends on unusually long mixing or narrow temperature control may have limited field value. Robustness trials should deliberately vary moisture, temperature, and delivery time within expected production limits.

Durability assessment should combine resistance to ingress with resistance to damage. Low permeability cannot compensate for wide through-cracks, poor cover, or defective joints. Similarly, crack control does not eliminate chemical transport through saturated pores. The material, reinforcement, detailing, workmanship,

drainage, and maintenance system should therefore be evaluated together when estimating asset performance.

Environmental claims require equivalent performance, compatible boundaries, and sensitivity analysis. Local transport, electricity, curing energy, replacement rate, and service life can change the result. The report should state whether carbon storage, allocation of industrial by-products, carbonation, maintenance, and end-of-life processes are included. Uncertain scenarios should be shown as ranges rather than hidden inside one precise-looking number.

A successful field program closes the loop between specification, production, verification, and asset monitoring. Prequalification establishes the feasible material envelope; acceptance testing controls delivered batches; inspection confirms construction quality; and periodic monitoring tests the service-life assumptions. Lessons from the asset should be returned to future mixture qualification, creating an evidence-based improvement cycle for sustainable civil engineering materials.