"Utilization of Plastic Solid Waste in Road Construction"

Asst. Prof. K. S. Redekar1 ,Swaraj Shinde2 ,Shubham Powar3

Asst. Prof. of department of civil engineering1, students BE department of civil Engineering2,3.

D. Y. PATIL TECHNICAL CAMPUS, FACULTY OF ENGINEERING AND MANAGEMENT TALSANDE, KOLHAPUR 416112

ABSTRACT

The increasing accumulation of plastic solid waste has become a major environmental challenge because most plastic materials decompose very slowly. Improper disposal of plastic waste contributes to land pollution, drainage blockage, and contamination of water bodies. At the same time, conventional road pavements may suffer from deformation, cracking, and deterioration due to traffic loads and changing environmental conditions.

The present study focuses on the utilization of plastic solid waste in flexible pavement construction. The main objective is to investigate the effect of incorporating waste plastic into bituminous mixtures and to evaluate the engineering properties of the resulting pavement material. In this investigation, three different plastic proportions, namely 4%, 8%, and 12%, are considered and compared with a conventional bituminous mixture containing no added plastic.

The performance of the prepared specimens is evaluated using the Marshall Stability and Flow Test. The test helps determine the load-bearing capacity and deformation characteristics of each mixture. The investigation also examines the potential environmental and economic benefits of using plastic waste in road construction. The most suitable plastic content will be identified based on the experimental results and the applicable mix-design requirements.

This project aims to demonstrate how suitable plastic solid waste can be utilized as a construction material while supporting improved waste management and sustainable infrastructure development.

The study also compares the stability and flow of the selected mixtures to understand how plastic content influences pavement behaviour. This approach may offer a practical way to reuse non-biodegradable plastic waste while potentially improving the performance and durability of flexible pavements.

Keywords: plastic Solid Waste, Road Construction, Flexible Pavement, Bituminous Mix, Waste Plastic, Marshall Stability, Marshall Flow, Sustainable Construction.

1. Introduction

Plastic is widely used in packaging, shopping bags, containers, household products, and industrial applications because it is lightweight, durable, and economical. However, the same durability that makes plastic useful also makes its disposal difficult. Large quantities of discarded plastic accumulate in landfills and other environments, creating long-term pollution problems.

Traditional waste-management methods may not be sufficient to manage all plastic waste effectively. Therefore, researchers are exploring ways to recover and utilize suitable plastic waste in construction and other engineering applications.

Road construction is one possible application because flexible pavements use aggregates and bitumen to form a durable road surface. Conventional bituminous mixtures can experience rutting, cracking, moisture damage, and other forms of deterioration under traffic and environmental conditions.

The incorporation of suitable waste plastic into bituminous mixtures may modify their engineering properties. Depending on the plastic type, preparation method, and quantity used, the modified mixture may demonstrate changes in stability, stiffness, bonding, and resistance to deformation.

The present project investigates the utilization of plastic solid waste in road construction using three plastic proportions: 4%, 8%, and 12%. The performance of these mixtures is compared with a conventional mixture to understand the influence of plastic content on the properties of flexible pavement material.

The study combines waste management with pavement-material evaluation and aims to identify a suitable plastic proportion through laboratory testing.

2. Objectives of the Study

1. To study the current use of plastic solid waste in road construction.
2. To understand the properties of the materials used in flexible pavement construction.
3. To investigate the effect of adding 4%, 8%, and 12% waste plastic to a bituminous mixture.
4. To prepare conventional and plastic-modified bituminous specimens.

3. LITERATURE REVIEW

Previous research has investigated the incorporation of waste plastic into bituminous mixtures to improve pavement properties and manage plastic waste.

3.1 Use of Waste Plastic in Bituminous Mixtures

Research on plastic-modified bituminous mixtures indicates that suitable plastic materials can influence the strength, stiffness, and deformation characteristics of pavement mixes. The performance depends on the polymer type, plastic content, mixing procedure, and aggregate-binder combination.

3.2 Evaluation Through Marshall Testing

The Marshall Stability and Flow Test is commonly used to evaluate the load resistance and deformation characteristics of compacted bituminous mixtures. Comparing conventional and modified mixtures helps determine how a selected additive influences the performance of the mixture.

3.3 Waste Plastic as a Construction Resource

Government guidance in India recognizes waste plastic as one of the solid waste materials that may be utilized in road projects under appropriate standards and specifications. The use of processed waste materials can help conserve natural resources and support more sustainable construction practices.

3.4 Research Gap and Present Study

The present project examines plastic contents of 4%, 8%, and 12%, rather than the 3%, 6%, and 9% proportions used in the reference paper. This provides a different set of experimental mixtures for evaluating the relationship between plastic content and bituminous mix performance.

The investigation will compare stability and flow values to identify whether the selected proportions produce satisfactory results under the laboratory conditions.

4. DETAILED THEORY OF FLEXIBLE PAVEMENT

4.1 Flexible Pavement

Flexible pavement is a multilayered road structure that distributes the loads of moving vehicles to the soil below. It consists of layers of different materials that work together to provide strength, stability, and a smooth riding surface.

The performance of flexible pavement depends on the properties of its constituent materials, the thickness of each layer, traffic intensity, drainage, and climatic conditions.

4.2 Components of Flexible Pavement

Subgrade: The subgrade is the natural soil that forms the foundation of the pavement. It must have sufficient strength to support the loads transferred from the upper layers.

Sub-base course: The sub-base is placed above the subgrade. It helps distribute loads and may provide drainage and additional support.

Base course: The base course is a structural layer that transfers traffic stresses toward the lower layers and supports the upper pavement structure.

Binder course: The binder course provides additional structural strength between the base and the wearing course where this layer is included in the pavement design.

Wearing course: The wearing course is the top layer that directly comes into contact with vehicle tyres. It provides a smooth surface and resists traffic abrasion, water penetration, and environmental exposure.

4.3 Role of Bitumen

Bitumen is a binding material that holds aggregate particles together. It provides cohesion and contributes to the flexibility of the pavement mixture.

However, bitumen properties are affected by temperature. At high temperatures, it may soften and contribute to rutting. At low temperatures, excessive stiffness may increase cracking susceptibility.

Suitable modification of the bituminous mixture may help address certain performance limitations. The effect must be verified through appropriate laboratory testing.

5. PLASTIC SOLID WASTE IN ROAD CONSTRUCTION

Plastic solid waste includes discarded packaging, bags, films, containers, and other plastic products. Some suitable plastic waste can be processed and incorporated into bituminous road materials.

Before use, the waste plastic must be appropriately segregated and processed. Its suitability depends on polymer type, cleanliness, particle size, and the method of incorporation.

Two general methods are used for incorporating plastic into bituminous mixtures.

5.1 Dry Process

In the dry process, processed plastic is introduced to heated aggregates according to the specified procedure. The plastic may form a coating on the aggregate surface before the binder is added.

The process aims to improve the interaction between the aggregate and the other mixture components.

5.2 Wet Process

In the wet process, a suitable plastic material is blended with the bitumen under controlled conditions before the modified binder is incorporated into the mixture.

The compatibility of the plastic with the binder and the required processing conditions must be considered.

The choice of process depends on the plastic type, laboratory facilities, and the applicable road-construction specifications. The actual method used in this project must be clearly stated in the final report.

6. MATERIALS REQUIRED

6.1 Bitumen

Bitumen acts as the binding material in the pavement mixture. The grade and quantity are selected according to the approved mix design.

6.2 Aggregates

Aggregates form the major part of the bituminous mixture and provide its structural framework. They should meet the required grading, strength, and quality specifications.

6.3 Waste Plastic

Suitable waste plastic is collected, segregated, and processed into the required particle size. The plastic type and its source should be recorded.

6.4 Mineral Filler

Mineral filler consists of fine particles that fill voids within the aggregate structure and influence the properties of the bituminous mixture.

6.5 Equipment

The laboratory equipment may include:

- Aggregate heating equipment.
- Bitumen heating equipment.
- Weighing balance.
- Mixing containers and tools.
- Marshall specimen moulds and compaction equipment.
- Marshall Stability testing machine.
- Flow-measuring equipment.
- Thermometer and other measuring instruments.

The exact equipment list should match the facilities used in the laboratory.

7. EXPERIMENTAL METHODOLOGY

7.1 Collection and Preparation of Materials

Aggregates, bitumen, and suitable waste plastic are collected for the experimental investigation. The aggregates are prepared according to the required grading, and the plastic is cleaned and processed as required by the selected method.

Four mixtures are considered in the investigation.

Specimen group	Plastic content
Conventional mixture	0%
Modified mixture A	4%
Modified mixture B	8%
Modified mixture C	12%

The basis of percentage calculation must be specified. For example, the plastic content may be expressed as a percentage by weight of bitumen or by weight of the total mixture. These bases are different and must not be mixed.

7.3 Preparation of the Mixture

The aggregates and bitumen are heated and mixed according to the approved laboratory procedure. The required quantity of processed plastic is incorporated using the selected method.

The mixing conditions should be controlled to achieve uniform distribution and avoid unnecessary overheating.

7.4 Preparation of Specimens

The prepared mixtures are placed in suitable moulds and compacted according to the selected Marshall Test procedure. The specimens are then cooled and prepared for testing.

The compaction effort, specimen dimensions, and preparation conditions should be consistent for all groups.

7.5 Marshall Stability and Flow Testing

Each specimen is tested using the laboratory's approved Marshall Stability and Flow Test procedure.

The maximum load carried by the specimen and its associated flow measurement are recorded. The required number of specimens is tested for each mixture, and the average values are calculated.

7.6 Comparison of Results

The results of the 4%, 8%, and 12% mixtures are compared with those of the conventional mixture. The comparison is used to evaluate how plastic content affects stability and flow under the specified test conditions.

8. MARSHALL STABILITY AND FLOW TEST

8.1 Marshall Stability

Marshall Stability is the maximum load a compacted bituminous specimen supports during the specified test.

It is generally expressed in kilonewtons (kN).

A higher stability value can indicate improved resistance to loading under the test conditions. However, stability must be evaluated alongside flow and other mix-design parameters.

8.2 Marshall Flow

Marshall Flow is the deformation associated with the maximum load in the prescribed test. It is commonly expressed in millimetres or the units used by the testing apparatus.
The flow value helps indicate the deformation characteristics of the mixture. The acceptable range depends on the applicable specification and the type of mix being investigated.

8.3 Importance of the Test

The Marshall Test helps compare the performance of conventional and plastic-modified mixtures. It provides experimental evidence for assessing whether the addition of waste plastic influences the stability and deformation characteristics of the mixture.

8.4 General Test Procedure

1. Prepare and compact the specimens using the selected mix-design procedure.
2. Record the identification and dimensions of each specimen.
3. Condition the specimens according to the applicable test method.
4. Position the specimen in the testing apparatus.
5. Apply the prescribed loading procedure.
6. Record the maximum load and corresponding flow.
7. Repeat the test for the required number of specimens.
8. Calculate the average stability and flow values for each plastic proportion.

9. Compare the results with the conventional mixture and relevant specifications.

9. RESULTS AND DISCUSSION

9.1 Experimental Observation Table

The following table should be completed using the actual laboratory readings.

Plastic content	Average specimen mass (g)	Marshall Stability (kN)	Marshall Flow (mm)
0% (Control)	1,200	8.20	2.60
4%	1,205	9.10	2.80
8%	1,210	10.00	3.10
12%	1,215	8.70	3.50

9.2 Stability Comparison

The measured stability values will be compared to understand the influence of plastic content on load resistance.

An increase in stability may indicate improved resistance to deformation under the test conditions. However, a decrease in stability at a higher plastic proportion may indicate that the selected plastic content or mixing conditions are unsuitable.

The conclusion must be based on actual test readings.




Figure 1: Marshall Stability of mixtures with 0%, 4%, 8% and 12% plastic content

9.3 Flow Comparison

The flow values will be compared to understand the deformation behaviour of each mixture. A suitable mixture must satisfy the applicable flow requirements. Neither the lowest nor the highest flow value should automatically be treated as the best result without considering the mix-design criteria.




Figure 2: Marshall Flow of mixtures with 0%, 4%, 8% and 12% plastic content

9.4 Identification of Suitable Plastic Content

The conventional mix and the three modified mixtures will be evaluated together. The most suitable proportion will be identified by considering:

- Marshall Stability.
- Marshall Flow.
- Other measured mix properties, where available.
- Compliance with the applicable specification.
- Workability and consistency of the prepared mixture.

The optimum content cannot be established until the experimental readings are available.

The optimum plastic content will be selected by comparing the stability and flow of each modified mixture with those of the conventional mixture, not by relying on a single value. The mixture with the highest Marshall Stability is not automatically the best, because its flow value must also fall within the permitted range. A high stability combined with very low or very high flow can indicate a brittle or an unstable mix. Other mix properties, such as bulk density, air voids, voids in mineral aggregate (VMA) and voids filled with bitumen (VFB), will also be checked where available, since they show how the plastic has changed the compaction and void structure of the mixture.

The selected mixture must satisfy the Marshall criteria of the applicable specification. For bituminous concrete, MoRTH specifications generally require a minimum stability of about 9 kN and a flow of 2–4 mm, but these limits should be verified against the specification edition used in this project. Workability and uniformity of mixing will also be recorded. If the plastic does not disperse evenly or the mix becomes difficult to compact at a higher content, that proportion may be rejected even if its stability is high. Based on the values in the current results table, the 8% mixture shows the highest stability (10.00 kN), while flow increases steadily with plastic content from 2.60 mm to 3.50 mm. This should be confirmed against the final laboratory readings before 8% is declared the optimum.

The paragraph uses the values in your 9.1 table, which your paper says are still to be replaced with real lab readings, so update it if those numbers change. I can insert it into section 9.4 and send you a new file if you'd like.




Figure 3: Combined trend of Marshall Stability and Flow with plastic content

9.5 Discussion of Sustainability

The use of suitable plastic solid waste in road construction may provide an additional outlet for certain discarded plastic materials. It can contribute to waste recovery and reduce the quantity of suitable waste requiring disposal.

However, its overall environmental value depends on collection, processing, emissions, durability, and end-of-life management.

10. ENVIRONMENTAL BENEFITS

Reduction in plastic disposal: The project investigates whether selected plastic waste can be utilized in a construction application rather than being discarded.

Resource conservation: The use of recovered waste material can support more efficient use of resources.

Support for sustainable infrastructure: The approach connects waste management with road-material development.

Potential reduction in pollution: Appropriate recovery and processing can reduce improper disposal of the plastic fraction used in the project.

These benefits depend on responsible material selection and processing. The project does not establish a quantified reduction in pollution unless supporting data are collected.

11. ECONOMIC BENEFITS

The use of plastic solid waste may offer economic advantages when suitable material is locally available and processing costs are reasonable.

Possible areas of benefit include:

1. Utilization of suitable recovered material.
2. Potential reduction in some conventional material requirements, depending on the mix design.
3. Possible maintenance savings if improved pavement performance is demonstrated.
4. Opportunities for organized collection and processing of plastic waste.

However, the actual economic benefit must be determined by considering collection, cleaning, shredding, transport, heating, equipment, labour, and quality-control costs. Cost savings should not be claimed without a supporting cost comparison.

12. LIMITATIONS OF THE STUDY

1. The investigation considers only the selected plastic contents and materials.
2. Different plastic types may produce different results.
3. The properties of the modified mixture depend on the mixing method and processing conditions.
4. Excessive plastic content may affect workability, flexibility, or mixture uniformity.
5. Marshall Stability and Flow results alone cannot establish long-term field performance.
6. Environmental impacts associated with heating, emissions, and pavement wear are not quantified unless separately investigated.
7. The experimental findings may not be directly applicable to every road type or climatic condition.

13. CONCLUSION

The present project investigates the utilization of plastic solid waste in road construction by incorporating 4%, 8%, and 12% plastic into selected bituminous mixtures. A conventional mixture is used as a reference to evaluate the effect of plastic addition.

The Marshall Stability and Flow Test provides a basis for comparing the load-bearing capacity and deformation characteristics of the prepared mixtures. The test results will help determine whether the selected plastic proportions produce satisfactory mixture properties under the laboratory conditions.

The project also highlights the potential role of waste-plastic utilization in supporting improved waste management and more sustainable road construction. However, the benefits depend on appropriate material selection, controlled processing, and compliance with relevant specifications.

The most suitable plastic content will be identified after evaluating the actual laboratory readings. The final conclusion should state which mixture provides the best overall balance of stability, flow, and other required properties.

Final experimental finding: The mixture containing [insert percentage] plastic showed the most suitable combination of stability and flow among the tested mixtures, based on the laboratory results and the applicable mix-design requirements.

14. FUTURE SCOPE

1. Investigate additional plastic contents to identify a more precise optimum proportion.
2. Study different plastic types separately to understand their individual effects.
3. Evaluate moisture resistance and resistance to permanent deformation.
4. Conduct fatigue and cracking tests to examine additional pavement properties.
5. Carry out field trials to assess long-term pavement performance.
6. Compare the life-cycle costs of conventional and modified pavement mixtures.
7. Evaluate the environmental effects of processing, construction, and pavement service life.
8. Study alternative processing techniques that may improve mixture uniformity and workability.

15. REFERENCES

1. Patil, S. V., Airekar, S. S., Pisal, A. A., Sathe, A. D., and Jadhav, A. S. (2026). “Performance Improvement of Flexible Pavement Using Waste Plastic.” International Journal of Research Publication and Reviews, Vol. 7, Issue 6, pp. 3306–3308. Reference paper supplied for this project.
2. Indian Roads Congress. (2013). IRC:SP:98-2013: Guidelines for the Use of Waste Plastic in Hot Bituminous Mixes (Dry Process) in Wearing Courses. https://law.resource.org/pub/in/bis/irc/irc.gov.in.sp.098.2013.pdf
3. Ministry of Road Transport and Highways, Government of India. “Use of Plastic Waste in Road

Construction." Press Information Bureau, 9 December 2019. https://rsdebate.nic.in/bitstream/123456789/704829/2/PQ_250_09122019_U2371_p356_p3 56.pdf.

4. ASTM International. ASTM D6927: Standard Test Method for Marshall Stability and Flow of Asphalt Mixtures. Use the edition followed by the laboratory. https://store.astm.org/d6927-22.html

5. Additional research articles on plastic-modified bituminous mixtures and sustainable road construction should be included after the specific papers have been reviewed and cited.