

Volume: 05 Issue: 05 | May - 2021

COMPARATIVE STUDY ON EFFECT OF DIFFERENT TYPES OF STEEL FIBERS ON STRENGTH PARAMETERS OF SELF COMPACTING CONCRETE

Prajakta Wadatkar ¹, Dr. S. G. Makarande ², Prof. R. S. Kedar ³

¹M.Tech student, Structural Engineering, Bapurao Deshmukh college of Engineering, Sewagram, Maharashtra

²Professor, Structural Engineering, Bapurao Deshmukh college of Engineering, Sewagram, Maharashtra

³Professor, Structural Engineering, Bapurao Deshmukh college of Engineering, Sewagram, Maharashtra

Abstract -The main objective of this research is analyze the effect of different types of steel fibers on strength parameters of self compacting concrete for M-40 grade of concrete by using fibers like straight fiber, crimped fiber and hooked fiber. Self-compacting concrete is a type of concrete which flows under the influence of gravity without segregation is used in reinforced structural members. It avoids the need of vibration. Steel fibers can resistance to crack, impact and fatigue resistance, reduce shrinkage and toughness. This project investigates the strength studies of self-compacting concrete using steel fibers as reinforcement to enhance. Various tests are to be performed to determine the properties of fresh and hardened concrete such as workability test, compressive test, flexure and tensile test of SSC containing fibers of 1%, 2% and3%, by volume of cement.

Key Words:self-compacting concrete, different types of steel fibers, M40 grade concrete, properties of fresh and hardened concrete...

1.INTRODUCTION

Self Compacting Concrete was first developed in Japan in the year 1980. Prof. H. Okamura of University of Tokyo, Japan; is mainly responsible for initiating and initial development of this concrete and is now regarded as the Father of SCC. The need for the development of SCC arose from the skilled labor and man power in Japan during 1980's. Self-compacting concrete has been represent "the most progressive improvement in concrete development". Self-compacting concrete is a concrete which exhibits good flow properties, good passing ability, and segregation resistance. No vibration is required to compact the concrete since the SCC has the capability of compacting under its own weight after being placed. it has proved to be beneficial for the Speedier development, Reduction in site labor, Better surface, Easier putting, Improved durability, Greater flexibility in outline, Thinner concrete sections, Reduced noise level, Safer working environment.

Self-Compacting Concrete often produced with lesser water-cement ratio yielding early strength and hence faster use of structures. Then, the elimination of vibrating equipment can reduce noise and vibrations. Moreover, to ensure high filling ability and flow without blockage, Self-Compacting Concrete should take lesser coarse aggregate contents and high cement content

which can increase the cost and temperature during hydration which leads to creep and shrinkage

The importance of self-compacting concrete is that maintains all concrete's durability and characteristics, expected performance requirements. meeting Compaction is hard to be done in conditions where there are dense reinforcement and large placing area. The addition of fibers in concrete upgrade the tensile strength, flexural strength, toughness, drying shrinkage, and failure pattern of the concrete. The Steel fiber concrete is a composite material made of cement, fine aggregate and coarse aggregates and steel fibers. In tension steel fiber concrete fails only after the steel fiber breaks out of the cement matrix. The Steel fiber concrete possess many dynamic performances such as high resistance to explosion and penetration as compared to traditional concrete.

Besides, depending on the structures, the use of steel fibers can reduce the required amount of conventional steel reinforcement. However, the addition of steel fibers into SCC may affect the fluid property of the concrete. Such as, if the fibers is increased in volume fraction and aspect ratio will decrease the flow of slump and ability to pass, while increasing the flow time of SCCSF. For that reason, this study helps to recognize the effect of selected steel fibers on the workability of SCC and how it can affect the hardened properties of concrete especially in mitigating crack propagation.

2. METHODOLOGY

The research work aims at studying the effect of straight fiber, crimped fiber and hooked fiber on strength parameters of self compacting concrete for M-40 grade of concrete having a mix proportion of 1:1.77:2.16 and maintaining water cement ratio =0.35. The mix design was carried out using IS:10262-2009. Cubes were casted and tested at 7 and 28 days in order to study the compressive strength of steel fiber self compacting concrete (SFSCC) containing this fibers at a varying percentage of 1%, 2% and 3% by volume of cement.

Three types of fibers with a different length, longitudinal shareware used in the investigation. Nine mixes contained combination of each fiber type with the amount equal to 1%, 2% and 3%. The analysis was focused on determination of the compressive and parameters of SFSCC mixes.

© 2021, IJSREM | www.ijsrem.com | Page 1

Volume: 05 Issue: 05 | May - 2021

2.1 Properties Of Used Materials-

<u>Cement-</u> Ordinary Portland cement (OPC) is by far the most important type of cement. It has adequate resistance to dry shrinkage and cracking, but has less resistance to chemical attack.

OPC 53 grade Ultra Tech cement is used in this experimental work confirming to IS12269-2013.

Property	Value	Standard value
	observed	for OPC
	in	
	investigat	
	ion	
Fineness (%)	5	Not exceed 10
Specific gravity	3.15	-
Consistency (%)	31	-
Initial setting	170min	>30
time(min)		
Final setting	280min	<600
time(min)		
Soundness (mm)	2.00	Not more than
		10mm
Compressive		
Strength	34.42	Not less than 27
3 Days	46.52	Not less than 37
7 Days	62.71	Not less than 53
28 days		

Table -1: Properties of Cement

<u>Fine Aggregate</u>- It may be natural sand, crushed stone or crushed gravel sand. The minimum particle size of fine aggregate is 0.075 mm and the maximum particle size is 4.75 mm.

Properties	Magnitude	Standard value as per Is 2386
Specific gravity	2.6	2.6-2.8
Grading zone	Zone II	-
Fineness modulus	2.8	2.6-2.9
Water absorption (%)	1.32	2

Table -2: Properties of Fine Aggregate

Coarse Aggregate- In project the aggregate passing from 20mm and retained on 10mm IS sieve are used.

Course aggregate confirming to IS code 383-1970 is used.

Properties	Coarse	Standard value as per
	aggregate	Is 2386
Particle size	20mm	
Particle shape	Angular	
Specific gravity	2.93	2.5-3.0
Bulk density	1340 kg/cu.m	1200 – 1750 kg/ cu.m
Fineness modulus	6.01	6 - 8
Water	0.42	2
absorption(%)		
Flakiness	22.13	25
index(%)		
Elongation	20.63	25
index(%)		
Impact value(%)	6.06	10
Crushing value(%)	19.63	-

ISSN: 2582-3930

Table -3: Properties of Coarse Aggregate

TYPES OF STEEL FIBERS

1. Straight Steel Fibers: Obtained by cutting drawn wires, and fibers with different types of indentations, and shapes to increase mechanical bond. Used for overlays and over slabbing for roads, pavements, airfields, bridge decks, and industrial and other flooring,



Fig -1: Straight Steel Fiber

Crimped Steel Fibers: The crimped steel fibers are made
of either carbon steel or stainless steel The crimped fiber
cross section may be circular and waving in cross
sections. The length of the fiber is normally less than 150
mm even though longer fibers have been used.



Fig -2: Crimped Steel Fiber

© 2021, IJSREM | www.iisrem.com | Page 2

Volume: 05 Issue: 05 | May - 2021

3. Hooked Steel Fibers: Cold-drawn hooked end steel fiber is manufactured by quality base steel bar, which has excellent mechanical properties including high tensile strength. Owing to high strength and uniform distribution of fibers, stresses can be fully dispersed and cracking propagation be effectively controlled.



Fig -3: Hooked Steel Fiber

<u>Water-It</u> is the very important and cheapest ingredient of concrete. The mixing water is utilized in the hydration of cement to form the binding matrix in which the inert aggregates are held in suspension until the matrix has hardened.

The remaining water serves as a lubricant between the fine and coarse and coarse aggregates and makes the concrete workable.

Admixture-Super Plasticizer: The purpose of Super Plasticizer is to improve the workability of fresh concrete. AUROMIX 400 INBNG1, a super plasticizer manufactured by FOSROC constructive solutions, was used in the present work.

Typical Properties of Auro-mix 400 Super Plasticizer

Properties	Result
Appearance	Light Yellow colored liquid
РН	Min 6
Volume mass @ 20°C	(1.09)Kg Per Liter
Chloride Content	Nil
Alkali content	< 1.5 g Na2o Proportionate liter of admixture

Table -4: Properties of Admixture

3. RESULTS AND DISCUSSION

In this project, the slump flow tests were conducted which is a primary testing on fresh concrete used in the field because of the ability to show the initial condition of the concrete mixture. This test show some information on the flowability and segregation of fresh SCC and SCCSF through measurement. As for the hardened concrete, the cubic specimens were moulded 24 hours after casting and then cured for 7 days and 28 days in water. Subsequently, the compressive tests were obtained to check the strength of the concrete.

ISSN: 2582-3930

3.1 Slump flow test- The slump flow test for fresh SCC and SCCSF were conducted in accordance with BS EN 12350-8-2010. Basically, the procedure begins with keeping the slump on plane platform. then filling the slump mould in a single layer without compaction and then the mould is raised immediately and slowly in a vertical direction. The value of the slump flow is the average of the largest slump flow diameter, d1 and the second diameter d2 that is perpendicular to the first measured diameter, d1. As per "The European Guidelines for Self Compacting Concrete" the acceptance criteria is between 550 mm and 850 mm.

Sr.	Types Of	Steel Fibre	Slump of
No.	Steel Fiber	Content	concrete
		(%)	in mm
1.	SCC	0 %	775
2.		1%	750
	Straight Fiber	2%	690
		3%	640
3.		1%	735
	Crimped Fiber	2%	685
	11001	3%	620
4.	Hooked Fiber	1%	720
		2%	660
		3%	620

Table -5: Slump Value

3.2 Compressive strength test- The compressive tests were conducted using the Compression Testing Machine with a capacity of 3000 kN. The test was performed based on the requirements by BS EN 12390-3:2009. This testgives the value of strength of all cubes specimens.

© 2021, IJSREM | www.ijsrem.com | Page 3







Volume: 05 Issue: 05 | May - 2021 ISSN: 2582-3930

Sr.	Types	Steel	Average Compressive	
No.	Of Steel	Fibre	strength N/Sq.mm	
	Fiber	Content		
		(%)	7 Days	28 Days
1.	SCC	0 %	32.89	44.08
_	Straight Fiber	1%	34.49	49.58
		2%	37.61	51.67
		3%	36.45	50.35
3.	Crimped Fiber	1%	35.68	50.58
		2%	38.41	52.33
		3%	40.84	53.17
4. Hook Fiber	Hooked Fiber	1%	37.89	51.23
		2%	41.12	53.79
		3%	45.72	55.38

Table -6: 7 and 28 days Compressive Strength



Graph -1: 7 Days Compressive Strength



Graph -2: 28 Days Compressive Strength

4. CONCLUSIONS

- 1. To establish this mix design in concrete, we obtained flowability test, passing ability test. Which show a positive result.
- From the result of workability it is observed that the workability decreases as the percentage of steel fibers increases.
- 3. The 7 and 28 days compressive strength of self-compacting concrete with hooked steel fibers at 3% is maximum.
- 4. Hooked steel fibers at 3% addition to SCC was found to be the most efficient mix.
- 5. The optimum percentage of different type of steel fiber was found to be 3 percentage for Hooked & crimped and 2 percentage for straight fiber.
- With increasing steel fiber content, mode of failure is changed from brittle to ductile when subjected to compression.
- 7. The addition of Steel Fiber in concrete delaying the propagation of cracking.

REFERENCES

- [1] Okamura H and Ouchi M 2003 Self-compacting concrete J AdvConcr Technol. 1(1), 5–15
- [2] European Project G 2005 The European guidelines for self-compacting concrete (United Kingdom)
- [3] Ding X, Li C, Han B, Lu Y and Zhao S 2018 Effects of different deformed steel-fibers on preparation and fundamental properties of self-compacting SFRC Constr Build Mater. 168 471–81
- [4] Aslani F and Nejadi S 2012 Bond characteristics of steel fiber and deformed reinforcing steel bar embedded in steel fiber reinforced self-compacting concrete (SFRSCC) Cent Eur J Eng. 2(3) 445–70
- [5] Grunewald S and Walraven J C 2001 Parameter-study on the influence of steel fibers and coarse aggregate content on the fresh properties of self-compacting concrete CemConcr Res. 31(12) 1793–8.
- [6] Madan S. K., Rajeshkumar G., and Sign S.P., "Steel Fibers as Replacement to Web Reinforcement for RCC Deep Beam in

© 2021, IJSREM | www.ijsrem.com | Page 4

International Journal of Scientific Research in Engineering and Management (IJSREM)

ISSN: 2582-3930



Volume: 05 Issue: 05 | May - 2021

- Shear", Asian journal of Civil Engineering Building and Housing), Vol. 8, No. 5 (2007), pp 479-489
- [7] DamgirR.M.andIshaque M.I.M (2003) "Effect of silica fume and steel fiber composite on strength properties of high performance concrete", proceeding of the INCONTEST 2003, Coimbatore, 10-12 sept 2003,pp281-286.
- [8] Raghuprasad .P.S, Ravindranatha (2003) "Experimental investigation on flexural strength of slurry infiltrated fiber concrete" proceeding of the INCONTEST 2003, Coimbatore, 10-12 sept 2003, pp 403-408
- [9] S.K. Madan, g. Rajesh Kumar and S.P. Singh, "Steel fibers replacement of web reinforcement for RCC deep beam in shear", Asian Journal of Civil Engineering (Building and Housing), Vol. 8, No. 56(2007), pp 479-489
- [10] Permalatha J and Govindraj V (2003) "Experimental studies on fiber reinforced concrete" "proceeding of the INCONTEST 2003, Coimbatore, 10-12 sept 2003, pp 462-468
- [11]Bayasi,Z and Zeng,J.(1993) "Properties of polypropylene fiber reinforced concrete" ACI Materials Journal, Novl-Dec 1993, vol. 90 No 6, pp 605-610
- [12]Soroushian P. and Bayasi (1991) "Fiber-type effect on the performance of steel fiber reinforced concrete" ACI Materials Journal, Mar-Apr 1991,vol 88 No 2,pp129-134
- [13]Ezeldin A.S and Lowe S.R (1991) "Mechanical properties of steel fiber reinforced rapid-set materials" "ACI Materials Journal, Jul-Aug 1991, vol. 88 No 4, pp384-389
- [14]IS: 456-2000, code of practice for plain and reinforced concrete, Bureau of Indian standards, New Delhi, India
- [16]IS: 10262-2004, Recommended guidelines for concrete mix design, Bureau of Indian standards, New Delhi, India
- [17] IS: 1489 (part-I)-2015, Portland pozzolana cement specification, Bureau of Indian standards, New Delhi, India
- [18] IS: 383-1970, specification for coarse and fine aggregate from natural sources for concrete, Bureau of Indian standards, New Delhi, India

© 2021, IJSREM | www.iisrem.com | Page 5